

Bezeichnung der Kunststoffe

Allgemein verwendete Bezeichnungen und Abkürzungen nach ISO 1043

Bezeichnung	Kurzzeichen
Acrylnitril-Butadien-Styrol-Pfropfcopolymerisat	ABS
Celluloseacetat	CA
Cellulosenitrat	CN
Ethylen-Chlortrifluorethylen-Copolymerisat	ECTFE
Ethylen-Tetrafluorethylen-Copolymerisat	ETFE
Tetrafluorethylen-Hexafluorpropylen-Copolymerisat	FEP
Glasfaserverstärktes, ungesättigtes Polyesterharz (UP)	GFK
Melamin-Formaldehyd-Harz	MF
Naturkautschuk/Naturgummi	NR
Polyamid	PA
Polycarbonat	PC
Polyethylen hoher Dichte (hart)	PE-HD
Polyethylen niedriger Dichte (weich)	PE-LD
Polyethersulfon	PES
Polyethylenterephthalat (Polyester)	PET
Perfluoralkoxy-Copolymerisat	PFA
Polymethylmethacrylat	PMMA
Poly-4-methylpenten-1	PMP (TPX [®])
Polyoxymethylen, Polyacetal	POM
Polyphenylensulfid	PPS
Polypropylen	PP
Polystyrol	PS
Polysulfon	PSU
Polytetrafluorethylen	PTFE
Polyurethan	PUR
Hart-PVC-Formmassen (unplasticized)	PVC-U
Weich-PVC-Formmassen (plasticized)	PVC-P
Polyvinylidenfluorid	PVDF
Styrol-Acrylnitril-Copolymerisat	SAN
Siloxan-Polymer (Silikon)	SI

Beständigkeitsliste

Definitionen und Abkürzungen

a = sehr gute Beständigkeit

bei Einwirkung von mehr als 30 Tagen keine oder nur geringe Schädigung.

b = bedingt beständig

bei längerer Einwirkung kann je nach Kunststoff eine Schädigung auftreten. (Haarrisse, mechanische Festigkeit, Verfärbungen, usw.)

c = unbeständig

kann zur Zerstörung des Kunststoffes, Deformation, usw. führen.

Hinweis

Sämtliche Informationen, Daten und Tabellen im technischen Teil und im Gesamtkatalog basieren auf Angaben und Unterlagen der Rohstoffhersteller oder unseren langjährigen Erfahrungen aus der Praxis. Sie verstehen sich ausdrücklich als Empfehlungen ohne Gewähr und befreien den Anwender unserer Produkte nicht, für den vorgesehenen Verwendungszweck jeweils eigene Prüfungen durchzuführen. Jeglicher Rechtsanspruch aufgrund der Angaben in diesen Unterlagen kann weder ausdrücklich, noch stillschweigend abgeleitet werden.

Unter Spannung stehende Teile können bei bestimmten Medien Festigkeitseinbussen erleiden (Spannungsrissbildung), obwohl sie gegen die Medien alleine beständig sind und ohne Einwirkung der Medien den Spannungen alleine standhalten würden. Dies ist besonders bei geschweissten Teilen zu berücksichtigen.

Alle Beständigkeitsangaben in diesem Katalog beziehen sich auf reine Stoffe. Bei Substanzmischungen können die Beständigkeiten wesentlich von den vorliegenden Angaben abweichen. Der Anwender hat dafür eigene Prüfungen durchzuführen.

Substanz	Konz.%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI			
Aluminiumnitrat	100	20	b	a	a	a	a	b	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	b	b			
		40	b	a	a	a	a	b	c	b	b	b	b	b	b	a	c	a	a	b	a	a	a	a	a	a	a	a	b	c	
		60	b	a	a	a	c	c	c	c	c	b	b	b	b	a	c	a	a	a	b	a	a	a	a	a	a	a	b	c	
Aluminiumoxid	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	b		
		40	b	a	a	a	a	b	c	b	b	b	b	b	b	a	c	a	c	a	b	a	a	a	a	a	a	a	b	c	
		60	b	a	a	a	c	c	c	c	c	b	b	b	b	a	c	a	a	a	b	a	a	a	a	a	a	a	a	b	c
Aluminiumsulfat	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	b		
		40	b	a	a	a	b	b	c	b	b	b	b	b	b	a	c	a	c	a	b	a	a	a	a	a	a	a	b	c	
		60	b	a	a	a	c	c	c	c	c	b	b	b	b	a	c	a	a	a	b	a	a	a	a	a	a	a	a	b	c
Aluminiumtrichlorid	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	b	b	
		40	a	a	a	a	b	b	a	c	b	a	a	a	b	a	c	a	a	a	a	a	a	a	a	a	a	a	a	b	b
		60	a	a	a	a	b	c	a	a	c	a	a	b	a	b	a	c	a	a	a	a	a	a	a	a	a	a	a	a	b
Ameisensäure	5	20	b	a	a	a	b	b	b	c	a	a	a	a	a	b	a	b	a	a	b	a	b	a	b	a	b	a	a	a	
		40	b	a	a	a	c	c	c		b	a	b	b	a	c	b	c	b	b	b	a	c	b	b	a	b	a	a	a	
		60	c	a	a	a					c	a	b	b	a	a	b	b	c	b	b	b	a	c	b	c	a	b	a	a	
	100	20	c	a	a	a	b	b	b	c	a	a	a	a	a	b	a	b	a	a	a	b	a	b	a	b	a	b	a	a	
		40		a	a	a	c	c	c		b	a	b	b	a	c	b	c	b	c	b	a	c	b	b	a	c	a	a	a	
		60		a	a	a					b	a	b	b	a	c	b	c	b	c	b	a	c	b	b	a	c	a	a	b	
Ameisensäureamid	100	20	c	a	a	a	a	a	b	b	a	a	a	a	a	c	a	a	a	c	b	a	a	b	b	a	c	b	a		
		40		a	a	a	b	b	b	b	b	a	b	b	a	b	a	b	b	b	b	a	b	b	c	b	a		b		
		60		a	a	a	b	b	c	c	b	a	b	b	a	b	a	b	b	b		c	a	b		c	a		b		
Aminobenzol	100	20	c	b	b	a	c	c	c	a	c	a	a	c	a	b	b	a	a	c	c	a	c	c	c	a	c	c	c		
		40		c	c	a				b	b	b	b	a	c	a	c	b	b	b	b	c	a	c	c	c	a	c	c		
		60				a				c		c	c		a	a	c	c	c			a					c				
Aminoessigsäure	10	20	a	a	a	a	a	b	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a	b		
		40	a	a	a	a	a	b	b	b	b	a	a	a	b	a	c	a	b	a	a	a	a	b	b	c	a	a	a	b	
		60	a	a	a	a	a	b	b	b	b	a	a	a	b	a	a	a	b	a	a	a	a	b	b	c	a	a	a	c	
Aminomethan	100	20	b	a	a	a	c	c	c	c	a	b	c	a	a	a	a	a	b	c	a	c	c	c	b	a	b	c			
		40	c	b	b	a					b	b		a	b	b	b	b	a	c	a			c	a	c					
		60		b	b	a					b	b		a	c	b	c	a					a				a				
Ammoniak	5	20	a	a	a	a	a	c	c	b	b	a	a	b	a	c	a	c	a	a	b	a	c	a	a	a	a	b			
		40	b	a	a	a	b			b	c	a	a	b	a		a		a	b	b	a		b	a	a	b	b			
		60	b	a	a	a	b			c	a	a	c	a	b	a		a		a	b	b	a		b	a	a	b	b		
	25	20	c	a	a	a	a	c	c	c	b	c	a	a	b	a	c	a	c	a	b	b	a	c	b	a	a	b	c		
		40		a	a	a	b			c		a	b	c	a		b		b	b	b	a		b	b	a	b				
		60		a	a	a	c					a	b	c	a		b		b	b	b	a		c	b	a	c				
	100	20	c	a	a	a	a	c	c	b	c	a	a	b	a	c	a	c	a	b	b	a	c	b	a	a	b	c	c		
		40		a	a	a	b			c		a	b	c	a		b		b	b	b	a		b	b	a	b				
		60		a	a	a	c					a	b	c	a		b		b	c	b	a		c	b	a	c				
Ammoniumacetat	50	20	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b		
		40	a	a	a	a	a	c	c	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	c		
		60	b	a	a	a	b			b	a	a	a	b	a	b	a	b	a	b	a	a	a	b	b	a	a	a			
Ammoniumalaun	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	c	a	c	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	a	b	b	b	a	a	a	a	a	a	a	a	a	b	a	a	a	b	b	a	b	a	a		
		60	c	a	a	a	b	b	b	c	b	a	a	b	a	b	a		a		a	c	b	a	c	b	b	a	c	b	
Ammoniumaluminiumsulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	c	a	c	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	a	b	b	b	a	a	a	a	a	a	a	a	a	b	a	a	a	b	b	a	b	a	a		
		60	c	a	a	a	b	b	b	c	b	a	a	b	a	b	a		a		a	c	b	a	c	b	b	a	c	b	
Ammoniumbicarbonat	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a		
		40	a	a	a	a	b	a	a	a	c	a	a	a	a	b	a	a	a	a	a	c	a	a	a	a	a	a	a		
		60	a	a	a	a	c	a	a	a	a	a	b	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
Ammoniumbiphosphat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	a	a		
		40	b	a	a	a	b	c	a		b	a	b	b	a	c	b	b	b	a	b	a	a	c	b	a	a	b	b		
		60	b	a	a	a	c			a		c	a	b	c	a		b	c	a	b	a	a		b	b	a	b	b		
Ammoniumcarbonat	100	20	a	a	a	a	a	a	a	a	a	b	a	a	a	c	a	c	a	a	a	a	a	b	b	a	a	b			
		40	b	a	a	a	b	b	a	b	b	a	b	b	a		a		a	b	a	a	b	b	b	a	b	c			
		60	c	a	a	a	b	b	a	c	b	b	c	b	a	b	a		a		a	c	a	b	c	c	a	c			
Ammoniumchlorid	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	a	b		
		40	b	a	a	a	b	b	a	b	b	a	b	b	a		a		a	b	a	a	b	b	b	a	b	c			
		60	b	a	a	a	c	b	a	b	b	b	b	b	a		a		a	b	a	a	c	b	b	a	b				
Ammoniumdihydrogenphosphat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	a	a		
		40	b	a	a	a	b	c	a		b	a	b	b	a	c	b	b	b	a	b	a	a	c	b	a	a	b	b		
		60	b	a	a	a	c			a		c	a	b	c	a		b	c	a	b	a	a		b	b	a	b	b		
Ammoniumfluorid	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	a	b		
		40	b	a	a	a	b	b	a	b	b	a	b	b	a		a		a	b	a	a	a	b	b	a	a	b	c		
		60	b	a	a	a	c	b	a	b	b	b	b	c	a		a		a	b	a	a	c	b	b	a	b				
Ammoniumhydrogencarbonat	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a		
		40	a	a	a	a	b	a	a	a	c	a	a	a	a	b	a	a	a	a	a	c	a	a	a	a	a	a	a		
		60	a	a	a	a	c	a	a	a		a	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a		
di-Ammoniumhydrogenphosphat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	a	a		
		40	b	a	a	a	b	c	a		b	a	b	b	a	c	b	b	b	a	b	a	a	c	b	a	a	b	b		
		60	b	a	a	a	c			a		c	a	b	b	c	a		b	c	a	b	a	a		b	b	a	b	b	
Ammoniumhydroxid	5	20	a	a	a	a	a	c	c	b	b	a	a	b	a	c	a	c	a	a	b	a	c	a	a	a	a	b			
		40	b	a	a	a	b			b	c	a	a	b	a		a		a	b	b	a		b	a	a	b	b			
		60	b	a	a	a	b					c	a	a	c	a		a		a	b	b	a		b	a	a	b	b		
	25	20	c	a	a	a	a	c	c	b	c	a	a	b	a	c	a	c	a	b	b	a	c	b	a	a	b	c			
		40		a	a	a	b			c		a	b	c</																	

Substanz	Konz.-%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
Ammoniumoxalat	100	20	a	a	a	a	a	a	b	b	c	a	a	a	a	a	b	b	a	a	a	a	a	b	a	a	a	b	
		40	a	a	a	a	a	a	b	a	c	b	a	a	a	a	c	b	b	a	a	a	a	b	b	a	a	a	c
		60	a	a	a	a	a	b	b	b	c	a	b	a	a	a	c	b	b	b	a	a	a	b	c	a	a	a	a
Ammoniumperoxodisulfat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	c	b	b	a	a	a	a	b	a	a	a	a	a	
		40	b	a	a	a	b	c	a		c	a	b	b	a	a		b		a	b	a	a	c	b	b	a	b	
		60	b	a	a	a	c		b			a	b	c	a			b		a	b	a	a	c	c	b	a	b	
Ammoniumpersulfat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	c	a	c	a	a	a	a	b	a	a	a	a	a	
		40	b	a	a	a	b	c	a		c	a	b	b	a	a		b		a	b	a	a	c	b	b	a	b	
		60	b	a	a	a	c		b			a	b	c	a			b		a	b	a	a	c	c	b	a	b	
mono-Ammoniumphosphat	100	20	a	a	a	a	a	b	a	c	b	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	a	
		40	b	a	a	a	b	c	a		b	a	b	b	a	a	c	b	b	a	b	a	a	c	b	a	a	b	
		60	b	a	a	a	c		a		c	a	b	c	a			b	c	a	b	a	a	b	a	a	a	b	
Ammoniumsulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	
		40	c	a	a	a	b	b	a	b	b	a	b	b	a	c	a	c	a	c	a	a	b	a	a	a	c	a	
		60	a	a	a	b	b	a	c	b	a	b	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	
Ammoniumsulfid	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	c	a	c	a	b	a	a	a	a	a	a	a	b	
		40	c	a	a	a	b	b	b	b	b	a	b	b	a		a		a	c	a	a	b	a	a	a	c	a	
		60	a	a	a	c	c	b	c	c	a	b	c	a			a		a		b	a	c	a	a	a	a	a	
Ammonnitrat	100	20	b	a	a	a	a	b	c	b	b	a	a	a	a	b	a	a	a	b	a	a	b	a	a	a	b	c	
		40	b	a	a	a	b	c		c	c	a	b	b	a	a	c	b	b	a	b	a	a	c	b	a	a	b	
		60	b	a	a	a	b					a	b	b	a			b	b	a	b	a	a		b	a	a	b	
Ammonsalpeter	100	20	b	a	a	a	a	b	c	b	b	a	a	a	a	b	a	a	a	b	a	a	b	a	a	a	b	c	
		40	b	a	a	a	b	c		c	c	a	b	b	a	a	c	b	b	a	b	a	a	c	b	a	a	b	
		60	b	a	a	a	b					a	b	b	a			b	b	a	b	a	a		b	a	a	b	
Ammonsulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	
		40	c	a	a	a	b	b	a	b	b	a	b	b	a	c	a	c	a	c	a	a	b	a	a	a	a	a	
		60	a	a	a	b	b	a	c	b	a	b	b	a			a		a		a	a	b	a	a	a	a	a	
Amylacetat	100	20	c	a	a	a	a	a	c	a	c	a	a	b	a	a	b	a	a	c	c	a	c	c	c	a	c	c	
		40	a	a	a	a	b		a		a	a	c	a	b	c	a	a				a					a		
		60	a	a	a	a	b		a		a	a	a	a	b			a		a			a				a		
Amylalkohol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	b	
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	b	
		60	b	a	a	a	c	a				a	a	c	a			b	a	a	b	a	a		c	a	b	b	
Anilin	100	20	c	b	b	a	c	c	a	c	a	a	c	a	b	b	a	a	c	c	a	c	c	c	a	c	c		
		40		c	c	a			b		b	b		a	c	b	b	b			a					b			
		60				a			c		c	c		a	c	c	c	c			a					c			
Anisol	100	20	c	a	a	a	b	c	c	a	c	b	b	a	c	c	c	c	b	c	c	a	c	c	c	a	c	c	
		40		b	b	a	c			b		b	c	c	a				b			a				b			
		60	b	b	a				b		b			a					b			a				b			
Anon	100	20	c	a	a	a	c	c	c	a	c	b	c	c	a	c	b	c	b	c	c	a	c	c	c	a	c	c	
		40	a	a	a				b		c			a		c			c			a				a			
		60	a	a	a				b					a								a				a			
Antimon(III)-chlorid	100	20	a	a	a	a	c	a	a	c	a	a	b	c	a	b	a	b	a	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a		b	b		b	b	c		a	c	b	b	a	b	a	a	a	a	b	a	a	b	
		60	b	a	a	a		b	b		b	b			a		b	c	a	b	a	a	a	a	b	b	a	b	
Antimontrichlorid	100	20	a	a	a	a	c	a	a	c	a	a	b	c	a	b	a	b	a	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a		b	b		b	b	c		a	c	b	b	a	b	a	a	a	a	a	b	a	a	b
		60	b	a	a	a		b	b		b	b			a		b	c	a	b	a	a	a	a	b	b	a	b	
Aqua Regia	100	20	c	a	a	a	c	c	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	
		40		b	b	a									a								a				b		
		60	c	c	a										a								a				c		
Arsen(V)-oxid Hydrat	100	20	a	a	a	a	a	b	b	b	a	a	b	a	a	c	a	c	a	a	b	a	b	a	a	a	a	b	
		40	b	a	a	a	b	c	b	c	b	a	c	b	a		b		a	b	c	a	c	b	b	a	b	b	
		60	b	a	a	a	b		b		c	b		b	a		b		a	b		a		b	b	a	b	b	
Arsensäure	100	20	a	a	a	a	a	b	b	b	a	a	b	a	a	c	a	c	a	a	b	a	b	a	a	a	a	b	
		40	b	a	a	a	b	c	b	c	b	a	c	b	a		b		a	b	c	a	c	b	b	a	b	b	
		60	b	a	a	a	b		b		c	b		b	a		b		a	b		a		b	b	a	b	b	
Ätzbaryt	100	20	a	a	a	a	a	b	a	a	c	a	b	a	a	c	b	c	b	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a	b	c	a	b		a	c	b	a		b		b	b	b	a	b	b	b	a	b	a	
		60	b	a	a	a	b		a	c		b		b	a		b		b	b	b	a	b	b	b	a	b	a	
Ätznatron	15	20	b	a	a	a	b	a	b	b	c	a	a	c	a	b	a	a	a	b	a	a	b	b	b	a	b	b	
		40	b	a	a	a	b	a	b	b		a	a		a	c	a	a	a	b	b	a	b	c	b	a	b	c	
		60	b	a	a	a	c	b	c	c		b	b		a		a	b	b	b	b	a	c		c	a	b		
	50	20	b	a	a	a	b	a	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	a	b	b	
		40	b	a	a	a	c	b		b		b	b		a		a		b	b	b	a	b	b	c	c	b	b	c
		60	c	a	a	a		c		c		c	c		a		a		c	c	b	a	c			b	c		
	100	20	b	a	a	a	b	b	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	a	b	b	
		40	c	a	a	a	c	c		c		b	b		a		a		b	c	b	a	a	c	c	c	b	c	c
		60	a	a	a							c	c		a		a		c		c	a				b			
Bariumcarbonat	100	20	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a	b	b	b	b	a	b	b	a	b	b	b	b	a	a	b	b	a	b	b	b	a	b	b
		60	b	a	a	a	b	c	b	c	b	a	c	b	a	b	b	b	a	a	b	b	a	c	c	b	b	a	b
Bariumchlorid	100	20	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a	b	b	a	b	a	a	b	b	a	b	b	a	a	b	b	a	b	b	b	a	b	a	b
		60	b	a	a	a	b	c	a	c	a	b	c	b	a	b	b	a	a	b	c	a	c	c	c	a	b	a	a
Bariumhydroxid	100	20	a	a	a	a	a	b	a	a	c	a	b	a	a	c	b	c	b	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a	b	c	a	b		a	c	b	a		b		b	b	b	a	b	b	b	a	b	a	
		60	b	a	a	a	b		a	c		b		b	a		b		b	b	b	a	b	b	b	a	b	a	
Bariumsulfat	100	20	a	a	a	a	a	a	a	c	a	a	b	a	a	b	a	b	a	a	a	a	a	a	b	b	a	a	
		40	a	a	a	a	a	b	a	b		a	c	a	a	c	a	b	a	a	a	a	a	a	c				

Substanz	Konz.-%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI		
Brommethan	100	20	c	a	a	a	c	c	c	b	c	b	b	c	a	c	b	c	b	c	c	a	c	c	a	c	c			
		40	b	b	b	a					c																			
		60		b	b	a										a							a							
Bromwasserstoffsäure	25	20	c	a	a	a	b	c	b	c	b	a	a	b	a	c	a	c	a	c	c	a	b	b	b	a	c	b		
		40		a	a	a	c		c			c	a	a	c	a		a					a	c	c	b	a	c	c	
		60		a	a	a							a	a		a		a					a			c	a			
1,3-Butadien	100	20	c	a	a	a	a	c	c	b	c	b	c	a	a	c	c	a	c	c	c	a	a	c	b	a	c	c		
		40		a	a	a	b				b		c		b	a							a	b		c	a			
		60		a	a	a	c				c				c	a							a	c		a				
Butan	100	20	b	a	a	a	a	c	c	a	c	a	b	a	a	b	a	b	a	b	a	a	a	b	a	a	b	c		
		40	b	a	a	a	b			a		a	b	b	b	a	c	b	b	b	b	b	a	b	b	a	a	b		
		60	b	a	a	a	b				b		b	c	b	a							b	b	b	a	a	b		
1,4-Butandicarbonsäure	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	c	a	b	b	b	b	b	a	b	c	b	a	b		
		40	b	a	a	a	b	a	a	a	a	a	b	b	a	a		a	b	a	a	b	a	b	a	a	a	b	b	
		60	c	a	a	a	b	a	a	b	b	a	b	b	a	a		a	c	a	a	b	a	b	a	a	a	b	b	
1,2-Butandiol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	b	c	c	a	a	c	b	
		40	a	a	a	a	b	a	a	a	b	a	a	b	a	a	b	a	a	a	a	a	a	b			a	a	a	
		60	a	a	a	a	c	a	a	a	c	a	a	c	a	c	a	b	a	a	a	a	a	c		c	a	a	a	
Butandisäure	100	20	c	a	a	a	a	b	b	a	a	a	a	a	a	c	a	c	a	c	a	a	a	a	a	a	c	b		
		40		a	a	a	b	c	c	b	b	a	a	b	a	b	a		a			b	a	b	b	b	a	a	c	
		60		a	a	a	b			b	b	a	a	b	a	b	a		a			b	a	b	b	b	a			
Butanol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	b		
		40	b	a	a	a		b	a	c	c	a	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	a	b	
		60	b	a	a	a		c	a			a	a	c	a	c	a	b	a	a	b		a			c	a	b	b	
2-Butanon	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	c	b	a	c	c	a	c	c	c	a	c	c		
		40		a	a	a	c			b		a	b			a			c	b			a				a			
		60		a	a	a				c		a	b			a				b			a					a		
Butansäure	100	20	c	a	a	a	a	c	c	b	c	b	c	a	a	b	c	a	c	c	b	a	c	c	b	a	c	c		
		40		a	a	a	a			c		c		b	a	c		a				b	a			c	a			
		60		a	a	a	b								c	a						a		b	a			a		
Butendisäure	100	20	b	a	a	a	b	a	c	b	c	a	b	a	a	b	b	b	a	b	c	a	c	a	a	a	b	b		
		40	c	a	a	a	b	b		b		a	b	b	a	c	b	c	a	c		a		b	b	b	a	c	c	
		60		a	a	a	c	b		c		a	c	c	a	c	a						a			b	b	a	c	c
Buttersäure	100	20	c	a	a	a	a	c	c	b	c	b	c	a	a	b	c	a	c	c	b	a	c	c	b	a	c	c		
		40		a	a	a	a			c		c			b	a	c		a			b	a			c	a			
		60		a	a	a	b								c	a						b	a				a			
Butylacetat	100	20	c	a	a	a	b	c	c	a	c	a	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	c		
		40		b	a	a	c			a		b	b	c	a		b	b	b			a					a			
		60		b	a	a				a		b	c	c	a		c	b	c				a					a		
Butylacrylat	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	b	c	b	c	c	a	c	c	c	b	c	c		
		40		a	a	a	b			a		a	a		a		b		c			a					b			
		60		a	a	a	c			b		b	a		a		c						a					c		
Butylalkohol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	b		
		40	b	a	a	a		b	a	c	c	a	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	a	b	
		60	b	a	a	a		c	a			a	a	c	a		b	a	a	b		a				c	a	b	b	
1,2-Butylenglykol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	b	c	c	a	a	a		
		40	a	a	a	a	b	a	a	a	b	a	a	a	b	a	a	a	a	a	a	a	a	b			a	a	a	
		60	a	a	a	a	c	a	a	a	c	a	a	a	c	a	b	a	a	a	a	a	a	c		c	a	a	a	
Butylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c		
		40		b	b	a		c		a		c			a							a				c	b			
		60		b	b	a				b						a							a				c	b		
2-tert.-Butylphenol	100	20	c	a	a	a	b	c	c	c	c	b	b	c	a	c	b	c	b	c	b	a	c	b	b	a	c	c		
		40		a	a	a	b					b	c			a		b		c		b	a		b	b	a			
		60		a	a	a	c									a		b				c	a			c	c	a		
Calciumacetat	100	20	b	a	a	a	a	a	a	a	b	a	a	a	a	a	b	a	b	a	b	b	a	a	a	a	b	a		
		40	b	a	a	a	b	a	a	a	c	a	a	b	a	c	a	a	b	a	b	b	a	b	b	a	a	b	a	
		60	b	a	a	a	c	a	a	b		a	a	c	a	a		a	b	a	b	b	a	c	b	a	a	b	a	
Calciumcarbonat	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	
		40	a	a	a	a	b	a	a	a	c	a	a	a	a	b	a	a	a	a	c	a	a	a	a	a	a	a	a	
		60	a	a	a	a	c	a	a	a		a	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Calciumchlorid	100	20	b	a	a	a	a	a	a	a	a	a	b	a	a	a	c	a	c	a	b	a	a	a	a	a	a	a	b	
		40	b	a	a	a	b	a	a	b	b	a	b	b	a		a				a	b	b	a	b	b	b	a	b	a
		60	b	a	a	a	c	a	a	c	c	b	c	b	a		b				b	b	c	a	c	b	b	a	b	a
Calciumhydroxid	100	20	b	a	a	a	a	a	a	a	c	a	a	a	a	a	c	a	c	a	b	b	a	b	a	a	a	b	a	
		40	b	a	a	a	b	a	a	b		a	a	b	a	b	a				a	b	b	a	b	b	a	a	b	a
		60	b	a	a	a	c	b	a	b		a	a	c	a		a				a	b	b	a	c	b	a	a	b	a
Calciumhypochlorit	100	20	b	a	a	a	a	c	c	c	c	a	a	a	a	a	c	a	c	a	b	a	a	a	b	b	a	b	a	
		40	c	a	a	a	b								a	b	a				a	c	a	a	b	c	b	a	c	a
		60		a	a	a	c						a	a	c	a		a				a	a	c			b	a		b
Calciumnitrat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	b	
		40	a	a	a	a	b	b	b	b	b	a	b	b	a						a	b	a	b	b	b	a	a	c	
		60	a	a	a	a	b	c	c	c	b	a	b	b	a		a					a	a	b	b	b	b	a	a	a
Calciumoxid	100	20	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	
		40	b	a	a	a	a	c	b	b	b	a	b	a	a	b	a	a	a	a	b	b	a	b	a	a	a	b	b	
		60	b	a	a	a	a			b	b	b	a	c	a	a	b	a	a	a	a	b	b	a	b	a	a	a	b	b
Calciumsulfat	100	20	c	a	a	a	a	b	b	c	a	a	a	a	a	a	c	a	c	a	c	a	a	a	a	a	a	c	b	
		40		a	a	a	b	b	b		b	a	b	b	a		a					b	a	b	b	b	a		b	
		60		a	a	a	b	b	b		b	a	b	b	a		a					b	a	b	b	b	a		b	
Campher	100	20	b	a	a	a	a	b	c	a	a	a	a																	

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI
			Carbamid	100	20	b	a	a	a	a	b	b	a	c	a	a	a	a	a	a	a	a	a	b	a	b	b	a
		40	b	a	a	a	a	b	c	a	c	a	a	a	a	a	a	a	a	a	b	a	b	c	a	a	b	
		60	c	a	a	a	b	c	c	a	c	a	a	b	a	c	b	a	a	b	c	a	b	c	a	a	c	
Carbolsäure	100	20	c	a	a	a	b	b	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	b	b	a	c	
		40		b	b	a	c	b							a						a	c	c	c	a	a	c	
		60		c	c	a		b							a						a				a		c	
Cetylalkohol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	a	b	b	a	a	a	
		40	a	a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	c	c	a	a	a	
		60	a	a	a	a	a	a	a	a	a	a	a	c	a	b	a	b	a	a	a	a			a	a	a	
Chlor	100	20	c	a	a	a	c	b	c	c	b	a	b	c	a	c	b	c	b	c	c	a	c	a	a	a	c	
		40		a	a	a		c			c	b	c		a		c		c			a		a	a			
		60		a	a	a									a							a		b	b	a		
3-Chlor-1-propen	100	20	c	a	a	a	c	c	c	c	c	b	b	c	a	c	b	c	b	c	c	a	c	c	c	b	c	
		40		a	a	a						b	c		a		c		b			a			b	b		
		60		a	a	a						c			a				c			a			c	c		
Chloralhydrat	100	20	c	a	a	a	a	c	c	c	b	b	b	c	a	c	b	c	b	c	c	a	c	b	a	a	c	
		40		a	a	a	b				c	b	b		a		c		c			a		c	b	a		
		60		a	a	a	c					c	c		a							a			b	a		
Chlorbenzol	100	20	c	a	a	a	b	c	c	a	c	b	c	c	a	c	b	c	b	c	c	a	c	c	c	a	c	
		40		b	b	a	c			b		b			a		c		c			a		c	a	c		
		60		c	c	a				c		c			a							a				a		
Chloressigsäure	100	20	b	a	a	a	b	c	c	c	c	a	a	c	a	c	a	c	a	b	c	a	c	c	b	a	b	
		40	c	a	a	a	c					a	a		a		b		b	c		a		c	a	c		
		60		a	a	a						a	a		a		b		b			a			a			
Chlorethan	100	20	c	a	a	a	c	b	b	b	c	b	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	
		40		a	a	a		b	c	c		b	c		a		c	b	c			a			a	a		
		60		a	a	a		b				b			a							a			a	a		
2-Chlorethanol	100	20	c	a	a	a	c	c	b	c	c	b	b	c	a	c	c	c	b	c	c	a	c	c	c	a	c	
		40		a	a	a			c			c	c		a				c			a				a		
		60		a	a	a									a							a				a		
Chlorethylen	100	20	c	b	b	a	b	b	c	c	c	b	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	
		40		b	b	a	b	b				c			a							a				a		
		60		c	c	a	c	c							a							a				a		
Chlormethan	100	20	c	a	a	a	a	c	c	b	c	a	a	c	a	c	b	b	b	c	c	a	b	c	c	c	c	
		40		b	b	a	a			b		b	b		a		c	b	b			a	b					
		60		b	b	a	a			c		b	c		a			b	c			a	c					
Chloroform	100	20	c	b	b	a	c	c	c	b	c	a	a	c	a	c	c	a	a	c	c	a	c	c	c	a	c	
		40		c	c	a				c		b	b		a			b	b			a				a		
		60				a						c	c		a			b	c			a				a		
Chlorsäure	25	20	c	a	a	a	b	c	c	c	b	a	a	c	a	c	a	c	a	c	c	a	c	a	a	a	c	
		40		a	a	a	c				c	a	a		a		a		a			a		a	a	a		
		60		b	a	a						a	a		a		a		a			a		b	a	a		
Chlorsulfonsäure	10	20	c	a	a	a	b	c	b	b	b	a	a	c	a	c	a	c	a	c	b	a	b	c	c	a	c	
		40		a	a	a	c		c	b	c	b	b		a		b		b		c	a	c		a	c		
		60		a	a	a					c	b	b		a		b		b			a			a			
	100	20	c	a	a	a	b	c	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	
		40		a	a	a	c								a							a				a		
		60		a	a	a									a							a				a		
Chlortoluol	100	20	c	a	a	a	b	c	c	c	c	b	b	c	a	c	c	a	c	c	c	a	c	b	b	a	c	
		40		a	a	a	c					c	c		a			b				a		c	c	a		
		60		a	a	a									a			c				a				a		
Chrom(VI)-oxid	100	20	b	a	a	a	a	c	c	c	b	a	a	a	a	c	a	b	a	b	a	a	c	b	a	a	b	
		40	c	a	a	a	b				c	a	a	b	a		a	c	a	c	b	a		b	a	a		
		60		a	a	a	b					a	a	b	a		a		a			b	a		a	c		
Chromsäureanhydrid	100	20	b	a	a	a	a	c	c	c	b	a	a	a	a	c	a	b	a	b	a	a	c	b	a	a	b	
		40	c	a	a	a	b				c	a	a	b	a		a	c	a	c	b	a		b	a	a		
		60		a	a	a	b					a	a	b	a		a		a		b	a		b	a	a		
Chromschwefelsäure	100	20	c	a	a	a	c	c	c	c	c	b	b	c	a	c	b	c	b	c	c	a	c	b	c	a	c	
		40		b	a	a					c	c			a		c		c			a		c	a			
		60		b	a	a									a							a			a			
Chromtrioxid	100	20	b	a	a	a	a	c	c	c	b	a	a	a	a	c	a	b	a	b	a	a	c	b	a	a	b	
		40	c	a	a	a	b				c	a	a	b	a		a	c	a	c	b	a		b	a	a		
		60		a	a	a	b					a	a	b	a		a		a		b	a		b	b	a		
Citronensäure	100	20	a	a	a	a	a	a	a	c	a	a	a	a	a	b	a	b	a	a	a	a	a	b	b	a	a	
		40	b	a	a	a	b	a	a		b	a	a	b	a	c	a	c	a	b	a	a	b	b	b	a	b	
		60	b	a	a	a	c	a	a		b	a	a	c	a		a		a	b	a	a	c	c	b	a		
Cumol	100	20	c	a	a	a	b	b	c	a	c	b	b	c	a	c	c	c	b	c	c	a	c	c	c	a	c	
		40		b	b	a	c	c			b	b	b	b	a							a				b		
		60		b	b	a					b		c		a							a				b		
Cyanwasserstoff	100	20	b	a	a	a	a	b	b	b	a	a	a	a	a	b	a	b	a	b	b	a	b	a	a	a	b	
		40	b	a	a	a	a	c	b	b	b	a	b	a	a	c	a	b	a	b	c	a	b	a	a	a		
		60	b	a	a	a	a		b	b	b	a	b	a	a		a	b	a	b		a	c	b	b	a		

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
			Cyclohexylalkohol	100	20	c	a	a	a	b	c	c	a	a	b	b	a	a	c	c	b	b	c	c	a	b	c	b	a
		40	a	b	b	a	c			a	b	c	c	c	a			c	c			a	c	c	c	a	c	c	
		60		b	b	a	c			a	b	c	c	c	a							a				a			
Decahydronaphtalin	100	20	c	a	a	a	c	b	b	a	c	a	b	c	a	b	c	a	b	c	c	a	c	c	a	a	c	c	
		40		a	a	a		c	c	a		b	b		a	c		b	b			a			b	a			
		60		a	a	a				a		b	c		a			b	c			a			c	a			
Decalin	100	20	c	a	a	a	c	b	b	a	c	a	b	c	a	b	c	a	b	c	c	a	c	c	a	a	c	c	
		40		a	a	a		c	c	a		b	b		a	c		b	b			a			b	a			
		60		a	a	a				a		b	c		a			b	c			a			c	a			
Decan	100	20	b	a	a	a	a	b	c	a	b	b	b	a	a	c	b	b	b	b	b	a	b	b	a	a	b	c	
		40	c	a	a	a	b	c		a	c	c	c	b	a		c	c	c	c	b	a	b	c	b	a	c		
		60		a	a	a	c			a					a						c	a	c		b	a			
DEHP	100	20	c	a	a	a	b	b	b	a	b	a	a	a	a	a	b	a	a	a	c	a	b	c	b	a	c	b	
		40		a	a	a	c	c	b	a	c	a	a	b	a	c	a	a	a			a	c		c	a	c		
		60		a	a	a		c	a		a	a	c	a	a		a	a	a			a			a				
Dextrin	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60	b	a	a	a	b	a	a	b	a	a	b	b	a	b	b	b	b	b	b	a	a	a	a	a	a	b	a
Dextrose	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Diacetonalkohol	100	20	b	a	a	a	a	b	c	c	a	b	c	a	a	b	a	b	a	b	c	a	c	c	c	c	b	c	
		40	b	b	b	a	b	b				a	c	a	a	c	a	a	b	b	b	a	a						
		60	c	b	b	a	c	c				a			a		a	c	c	c		a					c		
1,2-Diaminoethan	100	20	c	a	a	a	a	b	b	c	a	a	a	b	a	c	a	c	a	c	c	a	b	c	c	a	c	a	
		40		a	a	a	b	b	c		b	a	a	c	a		a					a	c			a	c	a	
		60		a	a	a	c	c			c	a	a	a	a		a		a			a				a	b		
Diammoniumsulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	b	a
		40	c	a	a	a	b	b	a	b	b	a	b	b	a	c	a	c	a	c	a	a	b	a	a	a	a	c	a
		60		a	a	a	b	b	a	c	b	a	b	b	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a
Dibutylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c	
		40		b	b	a		c		a		c			a							a			c	b			
		60		b	b	a				b					a							a				b			
1,2-Dichlorbenzol	100	20	c	a	a	a	b	c	c	a	c	b	c	c	a	c	b	c	b	c	c	a	c	c	c	a	c	c	
		40		b	b	a	c			b		b			a		c		c			a				a			
		60		c	c	a				c		c			a							a				a			
Dichloressigsäure	100	20	b	a	a	a	b	c	c	c	c	a	a	c	a	c	a	c	a	b	c	a	c	c	b	a	b	c	
		40	c	a	a	a	c					a	a		a		b		b	c		a			c	a	c		
		60		a	a	a						a	a		a		b		b			a			a				
1,2-Dichlorethan	100	20	c	a	a	a	c	c	c	a	c	c	c	c	a	c	c	a	c	c	c	a	c	c	b	a	c	c	
		40		a	a	a				a					a			b				a			c	a			
		60		a	a	a				a					a			c				a				a			
Dichlormethan	100	20	c	b	b	a	c	b	b	b	c	a	b	c	a	c	b	b	b	c	c	a	c	c	c	c	c	b	
		40		b	b	a		c	c	c		b	c		a		c	c	c			a					c		
		60		b	b	a						c			a							a							
Dieselmotorenöl	100	20	c	a	a	a	a	b	c	a	b	b	b	b	a	b	a	a	a	a	c	b	a	b	c	b	a	c	
		40		a	a	a	b	c		a	b	b	c	b	a	c	b	a	b			a	b	c	a	a			
		60		a	a	a	c			a	b	b		b	a		b	b	b			b	a	b		a			
Diethanolamin	100	20	b	a	a	a	a	b	a	a	c	b	c	b	a	b	b	b	a	b	b	a	b	c	c	c	b	b	
		40	c	b	b	a	b	c	a	b		c	c	a	c	c	b	b	b	c	c	a	c				c	b	
		60		b	b	a	c			a	b				a		b	b	c			a					c		
Diethylamin	100	20	b	a	a	a	a	b	a	a	c	b	c	b	a	b	b	b	a	b	b	a	b	c	c	c	b	b	
		40	c	b	b	a	b	c	a	b		c	c	a	c	c	b	b	b	c	c	a	c				c	b	
		60		b	b	a	c			a	b				a		b	b	c			a					c		
Diethylenglykol	100	20	b	a	a	a	b	a	a	a	b	a	a	b	a	b	a	a	a	b	b	a	b	b	b	a	b	b	
		40	b	a	a	a	c	a	b	a	c	a	a	c	a	b	a	b	a	b	b	a	c	c	c	a	b	c	
		60	b	a	a	a		b	c	a		a	a		a		a	c	a	b	b	a	b	b	a	a	b		
Diethylenoxid	100	20	c	a	a	a	b	b	b	a	a	b	b	b	c	a	c	b	b	c	b	c	a	b	b	b	c	b	
		40		b	b	a	b	b	c	b	b	b	b		a		b	c	b			b	a	b	c	c	c		
		60		b	b	a	c	c		b	c	b	c		a		c		c			c	a	c					
Diethylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c	
		40		b	b	a		c		a		c			a							a			c	b			
		60		b	b	a				b					a							a				b			
Diethylhexylphthalat	100	20	c	a	a	a	b	b	b	a	b	a	a	a	a	a	b	a	a	a	c	c	a	b	c	b	a	c	
		40		a	a	a	c	c	b	a	c	a	a	b	a	c	a	a	a			a	c		c	a	c		
		60		a	a	a			c	a		a	a	c	a		a	a	a			a				a			
Diethylketon	100	20	c	b	b	a	b	b	c	a	c	b	b	c	a	c	b	c	b	c	c	a	b	c	c	c	c	c	
		40		b	b	a	c	c		a		b	c		a		c		b			a	c						

Substanz	Konz.%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI		
2,6-Dimethyl-4-heptanon	100	20	c	b	b	a	b	b	c	a	c	b	b	c	a	c	b	c	b	c	c	a	b	c	c	c	c			
		40	a	b	b	a	c	c	a	a	c	b	c	c	a	a	c	c	b	c	c	a	c	c	c	c	c	c		
		60		c	c	a	c	c	a	a	c	b	c	c	a	a	c	c	b	c	c	c	a	c	c	c	c	c		
Dimethylamin	100	20	b	a	a	a	a	b	a	a	c	b	c	b	a	b	b	b	a	b	b	a	b	c	c	c	b	b		
		40	c	b	b	a	b	c	a	b	b	c	c	c	a	a	c	b	b	b	c	c	a	c	c	c	c	b	b	
		60		b	b	a	c		a	b						a	a	b	b	c	c	c	a	c				c	b	
1,4-Dimethylbenzol	100	20	c	a	a	a	a	a	c	a	c	b	b	a	a	c	b	b	b	c	c	a	a	c	c	a	c	c		
		40		b	b	a	a	b	a	a	c	b	c	b	a	a	c	c	c	c			a	a	c	c	a	c	c	
		60		b	b	a	a	b	a	a	c	a	c	c	c	a	a	c	c	c			a	a	c	c	a	c	c	
Dimethylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c		
		40		b	b	a		c	a	a	c					a	a						a		c	b	a	c	c	
		60		b	b	a			a	b						a	a						a			c	b	a	c	c
N,N-Dimethylformamid	100	20	c	b	b	a	c	b	b	b	c	a	a	c	a	c	a	c	a	c	c	a	c	c	b	c	c	c		
		40		b	b	a		c	c	c			a	a		a		a		a			a		c					
		60		b	b	a							a	a		a		a		a			a			c				
Dimethylsulfoxid	100	20	a	a	a	a	c	b	c	a	c	a	a	c	a	b	a	a	a	a	c	a	c	c	c	c	a	b		
		40		a	a	a	a		b		a		a	a		a	b	a	b	a	a		a					a	c	
		60		b	b	b	a		c		a		a	a		a	c	a	b	a	b		a					b		
Dinatriumtetraborat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a		
		40		a	a	a	a	b	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a	
		60		a	a	a	a	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	a	a	a	a	
Dioxan	100	20	c	a	a	a	b	b	b	a	b	b	b	c	a	c	b	b	b	c	b	a	b	b	b	c	c	b		
		40		b	b	a	b	b	c	b	b	b	b	a		a		b	c	b	c	b	a	b	c	c		c		
		60		b	b	a	c	c		b	c	b	c			a		c	c	c	c	c	a	c	c	b	a	c	c	
Diphenylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c		
		40		b	b	a		c	a	a	c					a							a		c	b	a	c	c	
		60		b	b	a			a	b						a							a			c	b	a	c	c
Diphenyloxid	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c		
		40		b	b	a		c	a	a	c					a							a		c	b	a	c	c	
		60		b	b	a			a	b						a							a			c	b	a	c	c
Dipropylenglykol	100	20	a	a	a	a	b	a	a	a	b	a	a	b	a	a	a	a	a	a	b	a	b	b	b	a	a	b		
		40		a	a	a	a	c	a	b	a	c	a	a	c	a	b	a	a	a	a	b	a	c	c	c	a	a	c	
		60		a	a	a	a		b	c	a	a	a	a	a	a	b	a	a	a	a	b	a	c	c	c	a	a	c	
Distickstoffoxid	100	20	c	a	a	a	c	b	c	b	c	b	c	c	a	c	a	b	b	c	c	a	c	c	c	a	c	c		
		40		b	b	a		b	c						a		b	c	c				a			a				
		60		b	b	a		c								a		c					a			a				
DMF	100	20	c	b	b	a	c	b	b	b	c	a	a	c	a	c	a	c	a	c	c	a	c	c	b	c	c	c		
		40		b	b	a		c	c	c			a	a		a		a		a			a		c					
		60		b	b	a							a	a		a		a		a			a			c				
DMSO	100	20	a	a	a	a	c	b	c	a	c	a	a	c	a	b	a	a	a	a	c	a	c	c	c	c	a	b		
		40		a	a	a	a		b		a		a	a		a	b	a	b	a	a		a				a	c		
		60		b	b	b	a		c		a		a	a		a	c	a	b	a	b		a				b			
Eisen(II)sulfat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	b		
		40		a	a	a	a	a	a	a	b	b	a	b	a	a	b	b	c	a	a	b	a	a	a	a	a	a	a	
		60		b	a	a	a	a	a	a	c	c	a	b	a	a	c	b		a	b	b	a	a	a	a	a	a	b	
Eisen(III)chlorid	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	b		
		40		b	a	a	a	a	a	a	b	b	a	b	a	a	c	b	c	a	b	a	a	b	a	a	a	a	b	
		60		b	a	a	a	a	a	a	c	b	a	b	a	a	a	b		a	b	a	a	b	a	a	a	a	b	
Eisen(III)nitrat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	b		
		40		b	a	a	a	a	a	a	b	b	a	b	a	a	b	b	c	a	b	b	a	a	a	a	a	b		
		60		b	a	a	a	a	a	a	c	c	a	b	a	a	c	b		a	b	b	a	a	b	a	a	a	b	
Eisenperchlorid	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	b	a	a	a	a	b		
		40		b	a	a	a	a	a	a	b	b	a	b	a	a	c	b	c	a	b	a	a	b	a	a	a	b		
		60		b	a	a	a	a	a	a	c	b	a	b	a	a	a	b		a	b	a	a	b	a	a	a	b		
Eisessig	100	20	b	a	a	a	b	a	b	c	b	a	a	b	a	c	a	c	a	b	b	a	b	b	a	a	b	b		
		40		c	b	b	a	c	b	c			c	a	a	c	a		a	c	c	c	a	c	c	b	a	c	c	
		60		c	c	a		c					a	a		a		a		a			a		c	a				
Erdöl	100	20	c	b	b	a	a	b	c	a	b	b	c	b	a	c	c	c	b	c	b	a	a	c	b	a	c	c		
		40		c	c	a	b	c			b	c	c		b	a				c		c	a	b	c	a				
		60				b	c			c					c	b							b	c		b				
Essigester	100	20	c	a	a	a	c	c	c	a	c	b	b	c	a	c	a	b	b	c	c	a	b	c	c	c	c	c		
		40		b	b	a				a		b	c		a		a	c	b			a	c							
		60		b	b	a				a		b				a		a		c			a							
Essigsäure	20	20	b	a	a	a	b	a	b	c	b	a	a	a	a	b	a	b	a	b	b	a	b	b	a	a	b	b		
		40		c	b	b	a	c	a	c	c	a	a	b	a	c	a	c	a	c	c	a	c	c	c	b	a	c	c	
		60		b	b	a		a					a	a	b	a	a		a				a		c	a				
	100	20	b	a	a	a	b	a	b	c	b	a	a	b	a	c	a	c	a	b	b	a	b	b	a	a	b	b		
		40		c	b	b	a	c	b	c			c	a	a	c	a		a	c	c	a	c	c	c	b	a	c	c	
		60		c	c	a		c					a	a		a		a		a			a		c	a				
Essigsäure Tonerde	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	b	a	a	a	a	a		
		40		a	a	a	a	b	b	b	b	a	a	a	a	a	b	a	c	a	b	a	a	c	a	a	a	a	a	
		60		a	a	a	a	c	c	b	b	a	a	b	a	a	c	a		a	b	a	a	c	a	a	a	a	b	
Essigsäurealdehyd	100	20	b	a	a	a	b	b	c	c	b	a	b	b	a	b	b	a	b	c	c	a	c	c	c	a	c	c		
		40		b	b	b	a	c	c				c	b	c	c	a	c	c	a	c		a			a				
		60		c	b	b	a	c					b			a		a					a				a			
Essigsäureallylester	100	20	b	a	a	a	b	c	b	c	b	a	a	b	a	c	a	b	a	b	b	a	b	b	b	a	b	a		
		40		c	a	a	a	c					c	a	a	c	a		b	c	a	c	c	a	c	c	b	a	c	a
		60		a	a	a								a	a		a		b		a		a				b	a	c	a
Essigsäureamid	100	20	a	a	a	a	a	a	c	a	c	a	a	b	a	c	a	a	a	a	c	a	a	c	c	a	a	c		
		40		a	a	a	a	a																						

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
			Essigsäureanhydrid	100	20	c	a	a	a	b	b	b	c	c	b	c	c	a	c	a	c	b	c	c	a	c	c	c	c
		40	a	a	a	a	c	c	c						a		a	c	b	c	c	a	c	c	c	a	c	a	
		60		a	a	a	c	c							a		b	c	c			a							
Essigsäurebenzylester	100	20	c	a	a	a	b	a	a	a	c	a	a	c	a	b	b	a	a	a	c	c	a	c	c	a	c	a	
		40	a	a	a	a	c	b	a	a	b	a	b		a	c	b	b	b	b	c	a	c	c	c	a	c	a	
		60	b	b	a	a	c	b	a	b		a	b		a		b	b	b			a				a	c	a	
Essigsäurebutylester	100	20	c	a	a	a	b	c	c	a	c	a	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	c	
		40	b	a	a	a	c			a	b	b	c	c	a		b	b	b			a				a	c	c	
		60	b	a	a	a	c			a	b	c	c	c	a		c	b	c			a				a	c	c	
Essigsäurechlorid	100	20	c	a	a	a	c	c	c	b	c	b	b	c	a	c	b	c	b	c	c	a	c	c	c	a	c	b	
		40	a	a	a	a	c			c	b	c	c		a		b	b	b			a				a	c	c	
		60	a	a	a	a	c								a		b		b			a				b	c	c	
Essigsäureethylester	100	20	c	a	a	a	c	c	c	a	c	b	b	c	a	c	a	b	b	c	c	a	b	c	c	c	c	c	
		40	b	b	a	a	c			a	b	c			a		a	c	b			a	c						
		60	b	b	a	a	c								a		a	c				a							
Essigsäuremethylester	100	20	c	a	a	a	c	c	c	a	c	b	b	c	a	c	a	b	b	c	c	a	b	c	c	c	c	c	
		40	b	b	a	a	c			a	b	c			a		a	c	b			a	c						
		60	b	b	a	a	c								a		a	c				a							
Essigsäurepentylester	100	20	c	a	a	a	a	a	c	a	c	a	a	b	a	a	b	a	a	a	c	c	a	c	c	a	c	c	
		40	a	a	a	a	a	b		a	a	a	c	a	a	b	c	a	a	a	c	a	c	c	c	a	c	c	
		60	a	a	a	a	a	b		a	a	a	a		a	b		a	a			a				a	c	c	
Essigsäurevinylester	100	20	c	b	b	a	b	b	c	c	c	b	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	
		40	b	b	a	b	b	b							a							a				a	c	c	
		60	c	c	a	c	c	c							a							a				a	c	c	
Ethanal	100	20	b	a	a	a	b	b	c	c	b	a	b	b	a	b	b	a	b	c	c	a	c	c	c	a	c	c	
		40	b	b	b	a	c	c			c	b	c	c	a	c	c	a	c			a				a	c	c	
		60	c	b	b	a	c	c				b			a			a				a				a	c	c	
1,2-Ethandiol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	a	b	b	a	a	a	a	
		40	a	a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	a	c	c	a	a	a	
		60	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	c	c	a	a	a	
Ethandisäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	a	c	
		40	a	a	a	a	a	a		a	b	b		a	a		b	b	c		b	a	b	a	a	a			
		60	a	a	a	a	a	a		a	c	c		b	a		c	c			c	a	c	a	a	a			
Ethanol	100	20	b	a	a	a	a	a	a	c	a	a	a	a	a	b	a	a	a	b	a	a	a	b	a	a	b	b	
		40	c	a	a	a	a	a			b	a	b	a	a	c	b	b	a	c	b	a	b	c	b	a	c	b	
		60	a	a	a	b	a	a			b	a	b	b	a	a	b	b	a		b	a	b	b	a	a	b	c	
Ethansäure	20	20	b	a	a	a	b	a	b	c	b	a	a	a	a	b	a	b	a	a	b	b	a	b	b	a	a	b	b
		40	c	b	b	a	c	a	c		c	a	a	b	a	c	a	c	a	c	c	a	c	c	b	a	c	c	
		60	b	b	a		a	a			a	a	b	a	a	a	a	a				a			c	a	a	c	
	100	20	b	a	a	a	b	a	b	c	b	a	a	b	a	c	a	c	a	b	b	a	b	b	a	a	a	b	
		40	c	b	b	a	c	b	c		c	a	a	c	a		a	c	a	c	c	a	c	c	b	a	c	c	
		60	c	c	a		c	c			a	a			a		a	a				a			c	a	a	c	
Ether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c	
		40	b	b	a	a	c	c		a	c				a							a			c	b			
		60	b	b	a					b					a							a				b			
Ethylacetat	100	20	c	a	a	a	c	c	c	a	c	b	b	c	a	c	a	b	b	c	c	a	b	c	c	c	c	c	
		40	b	b	a	a	c	c		a	b	c			a		a	c	b			a	c	c	c	c	c		
		60	b	b	a					a	b				a		a	c				a							
Ethylacrylat	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	b	c	b	c	c	a	c	c	c	b	c	c	
		40	a	a	a	b				a	a	a	a		a		b	c				a				b			
		60	a	a	a	c				b	b	a	a		a		c					a				c			
Ethylaldehyd	100	20	b	a	a	a	b	b	c	c	b	a	b	b	a	b	b	a	b	c	c	a	c	c	c	a	c	c	
		40	b	b	b	a	c	c			c	b	c	c	a	c	c	a	c			a				a	c		
		60	c	b	b	a	c	c				b			a			a				a				a	c		
Ethylalkohol	100	20	b	a	a	a	a	a	a	c	a	a	a	a	a	b	a	a	a	b	a	a	a	b	a	a	b	b	
		40	c	a	a	a	a	a			b	a	b	a	a	c	b	b	a	c	b	a	b	c	b	a	c	b	
		60	a	a	a	b	a	a			b	a	b	b	a	a	b	b	a		b	a	b	b	a	a	c	c	
Ethylbenzol	100	20	c	b	b	a	b	c	c	a	c	b	b	b	b	a	c	b	c	b	c	c	a	c	c	c	b	c	
		40	b	b	a	c				a	b	c	c	a		c		c				a				b			
		60	c	c	a					a	c				a							a				c			
Ethylchlorid	100	20	c	a	a	a	c	b	b	b	c	b	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	c	
		40	a	a	a		b	c	c		b	c			a		c	b	c			a				a			
		60	a	a	a		b				b				a		c					a				a			
Ethylenchlorhydrin	100	20	c	a	a	a	c	c	b	c	c	b	b	c	a	c	c	c	b	c	c	a	c	c	c	a	c	b	
		40	a	a	a	a	c	c				c	c		a		c	c				a				a	c		
		60	a	a	a										a							a				a	c		
Ethylenchlorid	100	20	c	a	a	a	c	c	c	a	c	c	c	c	a	c	c	a	c	c	c	a	c	c	c	b	a	c	
		40	a	a	a	a				a					a			b				a				a			
		60	a	a																									

Substanz	Konz.%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
Ethylentetrachlorid	100	20	c	c	c	a	a	b	c	a	c	b	c	a	a	c	c	a	c	c	c	a	a	c	c	a	c	c	
		40				b	a	b		a					a	b							b	a			a		
Ethyltrichlorid	100	20	c	a	a	a	c	b	c	a	c	b	c	b	a	c	c	c	c	c	c	a	b	c	c	a	c	c	
		40		b	b	a		b		a					a	b							b	a			a		
Ethylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	c	
		40		b	b	a		c		a					a	a							a			c	b		
Ethylmethylketon	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	c	b	a	c	c	a	c	c	c	a	c	c	
		40		a	a	a	c			b			a	b		a							a				a		
Ferrisulfat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	b
		40	b	a	a	a	a	a	a	b	b	a	b	a	a	a	b	b	c	a	a	b	a	a	a	a	a	a	b
Fette Öle	100	20	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b
		40	b	b	b	a	a	a	b	a	b	a	a	b	a	a	b	a	a	a	b	b	a	b	a	a	a	b	b
Flugbenzin	100	20	c	b	b	a	a	c	c	a	a	b	b	a	a	c	b	a	b	c	b	a	a	c	a	a	c	c	
		40		b	b	a	a			a	a	b	c	b	a			b	b	b	b	a	a			a			
Fluorkieselsäure	100	20	a	a	a	a	b	a	b	c	b	a	a	c	a	b	a	a	a	b	b	a	c	a	a	a	b	b	
		40	b	a	a	a	c	b	b		c	a	a	a	a	a	c	a	b	a	b	c	a	a	a	a	a	b	c
Fluorwasserstoffsäure	5	20	b	a	a	a	a	b	b	c	b	a	a	b	a	c	a	c	a	b	b	a	b	b	b	a	b	c	
		40	c	a	a	a	a	c	c		c	a	b	c	a		b	b	b	c	c	a	c	c	b	a	c		
Flusssäure	5	20	b	a	a	a	a	b	b	c	b	a	a	b	a	c	a	c	a	b	b	a	b	b	b	a	b	c	
		40	c	a	a	a	a	c	c		c	a	b	c	a		b		b	c	c	a	c	c	b	a	c		
Formaldehyd	10	20	b	a	a	a	a	b	b	b	a	a	a	a	a	a	a	a	a	b	b	a	b	b	b	a	b	b	
		40	c	a	a	a	a	b	b	b	b	a	a	b	a	b	a	b	a	a	c	b	a	b	c	b	a	c	c
Formalin	10	20	b	a	a	a	a	b	b	b	a	a	a	a	a	a	a	a	a	b	b	a	b	b	b	a	b	b	
		40	c	a	a	a	a	b	b	b	b	a	a	b	a	b	a	b	b	a	a	c	b	a	b	c	b	a	c
Formamid	100	20	c	a	a	a	a	a	b	b	a	a	a	a	a	a	c	a	a	a	c	b	a	a	b	b	a	c	b
		40		a	a	a	b	b	b	b	a	b	b	a	b	b	a	b	b	b	b	b	a	b	c	b	a	b	b
2-Furaldehyd	100	20	c	a	a	a	b	b	c	b	c	b	c	c	a	c	c	a	c	c	c	a	c	c	b	b	c	c	
		40		b	b	a	c	c		c					a								a			c	b		
Furfural	100	20	c	a	a	a	b	b	c	b	c	b	c	c	a	c	c	a	c	c	c	a	c	c	b	b	c	c	
		40		b	b	a	c	c		c					a								a			c	b		
Gerbsäure	100	20	b	a	a	a	a	b	c	a	b	a	a	b	a	c	a	c	a	b	b	a	a	b	b	a	b	b	
		40	c	a	a	a	a	b		b	c	a	b	c	a		b		b	c	c	a	c	c	b	a	c	c	
Gips	100	20	c	a	a	a	a	b	b	c	a	a	a	a	a	c	a	c	a	c	a	a	a	a	a	a	a	c	b
		40		a	a	a	b	b	b	b	a	a	b	b	a			a		a		b	a	b	b	b	a	b	
Glaubersalz	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40		a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Glucose	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Glycerin	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Glycin	10	20	a	a	a	a	a	b	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a	b
		40		a	a	a	a	b	b	b	a	a	a	b	a	c	a	b	a	a	a	a	b	b	a	a	a	a	b
Glykokoll	10	20	a	a	a	a	a	b	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	a	b
		40		a	a	a	a	b	b	b	a	a	a	b	a	c	a	b	a	a	a	a	b	b	a	a	a	a	b
Glykol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	b	b	a	a	a	c
		40		a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	a	c	c	a	a	a	a

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
Glykolsäure	100	20	b	a	a	a	a	a	c	a	a	a	a	a	a	b	a	a	a	b	a	a	b	b	b	a	b	a	
		40	b	a	a	a	a	a			a	b	a	a	b	a	c	a	a	a	b	b	a	b	c	b	a	b	a
		60	b	a	a	a	b	b			a	b	a	a	b	a	c	a	a	a	b	b	a	b	c	b	a	b	a
Harnsäure	100	20	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	
		40	b	a	a	a	a	b	c		a	b	a	a	b	a	c	a	b	a	b	a	a	b	b	a	a	b	a
		60	b	a	a	a	b	b			a	b	a	a	b	a	c	a	b	a	b	b	a	b	b	b	a	b	b
Harnstoff	100	20	b	a	a	a	a	b	b	a	c	a	a	a	a	a	a	a	a	a	b	a	a	b	b	a	a	b	
		40	b	a	a	a	a	b	c		a		a	a	b	a	b	b	a	a	b	c	a	b	c	c	a	b	b
		60	c	a	a	a	b	c			a		a	a	b	a	c	b	b	a	a	b	c	a	b	c	c	a	b
Heizöl	100	20	c	a	a	a	a	b	c	a	b	b	b	b	b	a	b	a	a	c	b	a	b	c	b	a	c	c	
		40		a	a	a	b	c			a	b	b	c	b	a	c	b	a	b		b	a	b		c	a		
		60		a	a	a	c					a	b	b	b	a	a	c	b	b			b	a	b			a	
Heptan	100	20	c	a	a	a	a	a	c	a	a	a	b	a	a	a	c	b	a	b	c	a	a	a	c	b	a	c	c
		40		a	a	a	a	b			a	b	b	c	a	a		b	b	b		b	a	b		c	a		
		60		a	a	a	a	b			a	b	c		a	a		c	b	c		b	a	b			a		
1-Hexadecanol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	b	a	a	a	a	b	b	a	a	a	a
		40	a	a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	a	c	c	a	a	a	a
		60	a	a	a	a	a	a	a	a		a	a	c	a	a	b	a	b	a	a	a	a			a	a	a	a
Hexadecansäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	a	c	c
		40		a	a	a	a	a			a	b	b		a	a		b	b	c		b	a	b	a	a	a		
		60		a	a	a	a	a			a	c	c		b	a		c	c			c	a	c	a	a	a		
Hexadecylalkohol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	a	b	b	a	a	a	a	a
		40	a	a	a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	c	c	a	a	a	a
		60	a	a	a	a	a	a	a	a	a		a	a	c	a	b	a	b	a	a	a	a			a	a	a	a
Hexafluorkieselsäure	100	20	a	a	a	a	b	a	b	c	b	a	a	c	a	b	a	a	a	b	b	a	c	a	a	a	a	b	b
		40	b	a	a	a	c	b	b		c	a	a		a	c	a	b	a	b	c	a			a	a	a	b	c
		60	c	a	a	a		b	b			a	a		a	a		a	c	a	c		a		b	a	a	c	
Hexahydrothymol	100	20	b	a	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	b	b	a	b	a	a	a	a	b	c
		40	b	a	a	a	b	a	a	b	b	a	b	b	a	b	b	b	b	a	b	b	a	b	b	b	a	a	b
		60	b	a	a	a	b	a	a	b	b	a	b	c	a	b	b	b	b	a	b	b	a	b	b	b	b	a	b
Hexan	100	20	c	a	a	a	a	b	c	a	b	b	c	a	a	c	b	a	b	c	a	a	a	c	b	a	c	c	
		40		a	a	a	a	c			a	c	b		b	a		c	a	b		b	a	a		c	a		
		60		a	a	a	a					a	c		b	a			a	c		b	a	b			a		
Hexandisäure	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	c	a	b	a	a	b	a	b	a	a	a	b	b	
		40	b	a	a	a	b	a	a	a	a	a	b	a	a		a	b	a	a	b	a	b	a	a	a	a	b	b
		60	c	a	a	a	b	a	a	b	b	a	b	b	a	a	b	a	c	a	a	b	a	b	b	b	a	a	c
Hexanol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	b	a	a	b
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	b	
		60	b	a	a	a		c	a			a	a	c	a	a	b	a	a	b		a			c	a	b	b	
1,2,6-Hexantriol	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		40	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	b	a	a	a	a
		60	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	c	b	a	a	a
Hexylalkohol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	b	b
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	b	
		60	b	a	a	a		c	a			a	a	c	a		b	a	a	b		a			c	a	b	b	
Hydrazinhydrat	100	20	c	b	b	a	b	c	c	c	c	c	c	c	a	b	c	b	c	c	c	a	c	c	c	c	c	c	
		40		b	b	a	c									a	c		c										
		60		c	c	a										a							a						
Hydrochinon	100	20	c	a	a	a	c	b	c	c	c	a	a	c	a	a	a	a	a	c	c	a	c	c	b	a	c	c	
		40		a	a	a		c				a	a		a	b	a	a	a			a			c	a			
		60		a	a	a						a	a		a	b	a	a	a			a				a			
4-Hydroxy-4-methyl-2-pentanon	100	20	b	a	a	a	a	b	c	c	c	a	b	c	a	b	a	b	a	b	c	a	c	c	c	c	b	c	
		40	b	b	b	a	b	b				a	c		a	c	a	b	b	b		a					b		
		60	c	b	b	a	c	c							a			a	c	c	c		a					c	
2-Hydroxybenzoesäure	100	20	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	b	a	a	a	
		40	a	a	a	a	b	a	c	b	b	a	a	b	a	a	b	a	a	a	a	a	a	b	b	b	a	a	b
		60	a	a	a	a	b	a			b	b	a	a	b	a	a	b	a	a	a	a	a	b	c	c	a	a	c
Hydroxyessigsäure	100	20	b	a	a	a	a	a	c	a	a	a	a	a	a	a	b	a	a	a	b	a	a	a	b	b	a	b	a
		40	b	a	a	a	a	b			a	a	a	a	b	a	c	a	a	a	b	a	a	b	b	b	a	b	a
		60	b	a	a	a	b	b			a	b	a	a	b	a	c	a	a	a	b	b	a	b	c	b	a	b	a
2-Hydroxypropansäure	100	20	a	a	a	a	a	b	b	b	b	a	a	a	a	a	b	a	b	a	a	a	a	b	b	b	a	a	b
		40	b	a	a	a	b	c	c	b	c	a	a	a	a	a	c	a	b	a	b	b	a	c	b	b	a	b	c
		60	b	a	a	a	b			c		a	a	b	a	b	a	a	b	a	b	b	a		b	b	a	b	
2,2'-Iminoethanol	100	20	b	a	a	a	a	b	a	a	c	b	c	b	a	b	b	b	a	b	b	a	b	c	c	c	b	b	
		40	c	b	b	a	b	c	a	b		c		c	a	a	c	b	b	b	c	c	a	c			c	b	
		60		b	b	a	c			a	b					a		b	b	c		a							c
Iod	100	20	c	a	a	a	b	b	c	c	c	c	c	c	a	c	b	c	b	c	c	a	c	c	c	a	c	c	
		40		b	b	a	c	c								a		c		c									
		60		b	b	a										a							a						
IPA	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	
		40	b	a	a	a	a	a	a	c	a	a	a	b	a	b	a	a	a	b	a	a	a	c	b	a	b	a	
		60	b	a	a	a	a	a	a			a	a	a	c	a	b	a	a	b	a	a	a		b	a	b	a	
Isobutylalkohol	100	20	b	a	a	a	a	a	a	c	a	a	a	a	a	b	a	a	a	b	a	a	a	b	a	a	b	a	
		40	b	a	a	a	a	b	a			b	a	a	b	a	b	b	a	a	b	b	a	b	c	b	a	b	a
		60	b	a	a	a	a	b	b			b	a	a	b	a	b	b	a	a	b	b	a	b		b	a	b	b
Isooctan	100	20	c	a	a	a	b	a	a	a	b	a	a	a	a	a	b	a	a	a	c	b	a	b	c	b	a	c	a
		40		a	a	a	c	b	b	a	c	a	a	b	a	b	a	a	a	a		c	a	c		c	a		b
		60		a	a	a		c	c	a		a	a	b	a	b	a	a	a	a			a				a		c

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI			
Kaliumhydroxid	50	20	b	a	a	a	b	a	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	b	b	b			
		40	b	a	a	a	a	c		b	c		c	c		a		a		c	c	b	a	c	c	c	b	c	c		
		60	c	a	a	a	a	c			c		c	c		a		a		c	c	b	a	c	c	c	b	c	c		
	100	20	b	a	a	a	b	b	c	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	b	b	b		
		40	c	a	a	a	c	c		c	c		b	b		a		a		c	c	b	a	c	c	c	b	c	c		
		60	a	a	a	a							c	c		a		a		c	c	a	a	c			b				
Kaliumiodid	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a			
		40	b	a	a	a	b	b	b	c	b	a	a	a	b	a	b	a	a	a	b	b	a	b	b	b	a	b	b		
		60	b	a	a	a	a	c		b	c	c	a	a	c	a	a	b	a	a	a	b	a	c	b	b	b	a	b	b	
Kaliumnitrat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a		
		40	a	a	a	a	a	a	a	c	b	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	a	b	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	
Kaliumperchlorat	25	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a		
		40	a	a	a	a	a	a	b	b	b	b	a	a	b	a	b	b	b	a	a	b	a	b	a	a	a	a	b	b	
		60	a	a	a	a	a	a	b	b	c	a	a	a	b	a	b	b	b	a	a	b	a	b	a	a	a	a	a	b	b
Kaliumpermanganat	100	20	b	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a		
		40	c	a	a	a	a	a	b		b	a	a	b	a	b	b	b	a	b	c	b	a	b	b	b	a	c	b	b	
		60	a	a	a	a	a	b	c		c	a	a	c	a	b	b	b	a	b	c	a	c	c	c	b	a	a	c	c	
Kaliumperoxodisulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	a	a	a	b	b	a	b	c	a	c	b	b	a	b	b	a	b	b	b	b	a	b	a	b	
		60	b	a	a	a	a	a	a	c	c	a	b		a		b	b	a	b	c	a	c	b	b	b	a	b	a	b	
Kaliumpersulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	a	a	a	b	b	a	b	c	a	c	b	b	a	b	b	a	b	b	b	b	a	b	a	b	
		60	b	a	a	a	a	a	a	c	c	a	b		a		b	b	a	b	c	a	c	b	b	b	a	b	a	b	
Kalk	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	
		40	a	a	a	a	b	a	a	a	c	a	a	a	a	a	b	a	a	a	a	c	a	a	a	a	a	a	a	a	a
		60	a	a	a	a	c	a	a	a	a	a	b	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Kalk gebrannt	100	20	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	
		40	b	a	a	a	c	b	b	b	a	b	a	a	b	a	b	a	a	a	b	b	a	b	a	a	a	a	b	b	
		60	b	a	a	a	a		b	b	b	a	c	a	a	b	a	b	a	a	a	b	b	a	b	a	a	a	b	b	
Kampfer	100	20	b	a	a	a	a	b	c	a	a	a	a	a	a	b	a	a	a	b	a	a	a	c	b	a	b	c			
		40	b	a	a	a	b	c		a	b	a	b	b	a	c	a	b	a	b	b	a	b		c	a	b				
		60	c	a	a	a	b			b	b	a	b	b	a	a	a	b	a	a	c	b	a	b			a	c			
Kerosin	100	20	c	b	b	a	a	c	c	a	a	b	b	a	a	c	b	a	b	c	b	a	a	c	a	a	c	c	c		
		40		b	b	a	a			a	a	b	c	b	a		b	b	b		b	a	a		a	a					
		60		c	c	a	a			a	a	b		b	a		c	b	c		c	a	a		a	a					
Kieselsäure	100	20	b	a	a	a	a	b	b	a	a	a	b	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	b	c	c	b	b	a	c	b	a	c	b	c	a	b	b	a	b	b	b	b	a	b	b		
		60	c	a	a	a	b			c	c	a		b	a		b		a	c	c	a	c	b	b	a	c	c	c		
Kochsalz	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
Kohlendioxid	100	20	b	a	a	a	a	b	b	a	a	a	b	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	b	c	c	b	b	a	c	b	a	c	b	a	c	a	b	b	a	b	b	b	a	b	b		
		60	c	a	a	a	b			c	c	a		b	a		b		a	c	c	a	c	b	b	a	c	c	c		
Kohlensäure	100	20	b	a	a	a	a	b	b	a	a	a	b	a	a	b	a	b	a	b	a	a	a	a	a	a	a	b	a		
		40	b	a	a	a	b	c	c	b	b	a	c	b	a	c	b	c	a	b	b	a	a	b	b	b	a	b	b		
		60	c	a	a	a	b			c	c	a		b	a		b		a	c	c	a	c	b	b	a	c	c	c		
Kohlenstoffdisulfid	100	20	c	a	a	a	c	b	c	a	c	c	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	c		
		40		b	b	a		c		b					a								a				a				
		60		c	c	a				c					a								a				a				
Königswasser	100	20	c	a	a	a	c	c	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	c		
		40		b	b	a									a								a				b				
		60		c	c	a									a								a								
Kreide	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a		
		40	a	a	a	a	b	a	a	a	c	a	a	a	a	a	b	a	a	a	a	c	a	a	a	a	a	a	a	a	
		60	a	a	a	a	c	a	a	a	a	b	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
p-Kresol	100	20	c	a	a	a	b	c	c	c	c	b	c	c	a	c	c	c	c	b	c	c	a	c	c	c	a	c	c		
		40		b	b	a	c					c				a				c			a				a				
		60		b	b	a							c			a					c			a				a			
Kupfer(I)cyanid	50	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	b	a	b	a	a	b	a	b	a	a	a	a	a		
		40	a	a	a	a	a	a	a	b	c	a	a	a	a	a	c	a	c	a	a	c	a	c	a	a	a	a	a	a	
		60	a	a	a	a	a	b	b	b		a	a	b	a		a			a	a		a		a	a	a	a	a	b	
Kupfer(II)chlorid	100	20	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a		
		40	a	a	a	a	a	b	c	c	b	a	a	a	a	a	b	a	a	a	a	a	b	a	b	b	b	a	a	c	
		60	b	a	a	a	b	b			b	b	b	a	b	a	b	b	b	a	b	c	a	b	c	c	a	b			
Kupfer(II)nitrat	100	20	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a		
		40	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	
Kupfer(II)sulfat	100	20	b	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	b	a	a	a	a	a	a	a	a	b	a	
		40	b	a	a	a	a	a	a	b	b	a	b	c	a	c	b	b	a	b	b	a	a	b	b	b	a	b	a	b	
		60	b	a	a	a	a	a	a	c	c	a	b	c	a		a			b	b	a	b	c	a	c	b	b	a	b	a
Kupfervitriol	100	20	b	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	b	a	b	a	a	a	a	a	a	b	a	
		40	b	a	a	a	a	a	a	b	b	a	b	c	a	c	b	b	a	b	b	a	b	b	b	b	a	b	a	b	
		60	b	a	a	a	a	a	a	c	c	a	b	c	a		a			b	b	a	b	c	a	c	b	b	a	b	a
Lanolin	100	20	a	a	a	a	a	a	a	a	a	b	a	a	a	a	b	a</													

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
			Leuchtpetrol	100	20	c	b	b	a	a	c	c	a	a	b	b	a	a	c	b	a	b	c	b	a	a	c	a	a
		40		b	b	a	a			a	a	b	c	b	a		b	a	b	c	b	a	a	a	a	a			
		60		c	c	a	a			a	a	b	b	b	a		c	b	c		c	a	a		a	a			
Magnesiumcarbonat basisch	100	20	b	a	a	a	a	a	a	a	a	a	b	a	a	a	b	a	a	b	a	a	a	b	b	a	b	a	
		40	b	a	a	a	a	a	a	a	a	b	b	b	a	a	b	a	a	b	a	a	a	b	b	a	b	a	
		60	b	a	a	a	a	a	a	a	a	b	b	b	a	a	b	b	a	b	a	a	a	b	b	a	b	a	
Magnesiumchlorid	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	b	b	a	b	a	
		40	b	a	a	a	a	a	a	b	b	a	b	b	a	c	b	c	a	b	b	a	b	b	b	a	b	a	
		60	b	a	a	a	a	a	a	b	b	a	c	b	a		b	a	a	b	b	a	b	b	b	a	b	a	
Magnesiumhydroxid	100	20	b	a	a	a	a	a	a	a	a	a	a	c	a	b	a	a	a	b	a	a	a	a	a	a	b	a	
		40	c	a	a	a	a	b	a	b	b	a	a		a	c	a	a	a	c	b	a	b	a	a	a	c	a	
		60		a	a	a	a	b	b	c	c	a	b		a		b	a	a		c	a	c	b	a	a	a	a	
Magnesiumhydroxidcarbonat	100	20	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	b	b	a	b	a	
		40	b	a	a	a	a	a	a	a	a	b	b	b	a	b	b	a	a	b	a	a	a	b	b	a	b	a	
		60	b	a	a	a	a	a	a	a	a	b	b	b	a	b	b	a	a	b	a	a	a	b	b	a	b	a	
Magnesiumnitrat	100	20	b	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	b	a	a	a	a	b	a	a	b	a
		40	c	a	a	a	a	b	a	b	b	a	a	b	a	c	a	a	a	c	b	a	b	a	a	a	c	a	
		60		a	a	a	a	b	b	c	c	a	b	c	a		b	a	a		c	a	c	b	a	a	a	a	
Magnesiumsulfat	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	b	a	
		40	c	a	a	a	a	a	b	b	b	a	a	b	a	c	a	b	a	c	b	a	b	b	b	a	c	a	
		60		a	a	a	a	b	b	c	c	a	b	c	a		b	b	a		c	a	c	c	c	a	a	a	
Maleinsäure	100	20	b	a	a	a	b	a	c	b	c	a	b	a	a	b	b	b	a	b	c	a	c	a	a	a	b	b	
		40	c	a	a	a	b	b		b		a	b	b	a	c	b	c	a	c				b	b	a	c	c	
		60		a	a	a	c	b		c		a	c	c	a		c		a				a	b	b	a			
Maschinenöl	100	20	b	a	a	a	a	b	c	a	a	a	b	a	a	b	a	b	a	b	a	a	a	a	c	b	a	b	b
		40	b	a	a	a	b	b		a	b	b	c	b	a	c	b	c	b	b	a	a	a	b	b	a	b	c	
		60	c	a	a	a	b	c		a	b	b		b	a		b		b	c	a	a	b		c	a	c		
MEK	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	c	b	a	c	c	a	c	c	c	a	c	c	
		40		a	a	a	c			b		a	b		a			c	b			a				a			
		60		a	a	a				c		a	b		a				b			a				a			
Menthol	100	20	b	a	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	b	b	a	b	a	a	a	b	c	
		40	b	a	a	a	b	a	a	b	b	a	b	b	a	b	b	b	a	b	b	a	b	b	b	a	b		
		60	b	a	a	a	b	a	a	b	b	a	b	c	a	b	b	b	a	b	b	a	b	b	b	a	b		
Methacrylsäureester	100	20	c	b	b	a	a	c	c	a	a	b	c	b	a	c	c	c	c	c	c	a	c	a	a	a	b	c	
		40		b	b	a	b			b	b	c		c	a							a		a	a	c			
		60		b	b	a	b			b	b				a							a		b	a				
Methanal	10	20	b	a	a	a	a	b	b	b	a	a	a	a	a	a	a	a	a	b	b	a	a	b	b	b	a	b	
		40	c	a	a	a	a	b	b	b	b	a	a	b	a	b	b	a	a	c	b	a	b	c	b	a	c	c	
		60		a	a	a	b	b	b	c	b	a	a	c	a	c	b	b	a		c	a	c		c	a			
	40	20	c	a	a	a	a	a	b	b	a	a	a	b	a	c	a	a	a	c	b	a	a	b	b	b	a	c	
		40		a	a	a	b	b	b	b	b	a	b	b	a		b	b	b		b	a	b	c	b	a	b		
		60		a	a	a	b	b	c	c	b	a	b	c	a		b	b	b		c	a	c		c	a	b		
Methanol	100	20	b	a	a	a	b	a	a	c	b	a	a	a	a	b	a	b	a	b	b	a	a	b	b	a	a	b	
		40	c	a	a	a	c	a	a		c	a	a	b	a	c	a	b	a	c	c	a	c	c	b	a	c	b	
		60		a	a	a		a	b			a	a	c	a		a	b	a			a		b	a	a	b		
Methansäure	5	20	b	a	a	a	b	b	b	c	a	a	a	a	a	b	a	b	a	a	b	a	b	a	b	a	a	a	
		40	b	a	a	a	c	c	c		b	a	b	b	a	c	b	c	b	b	b	a	a	c	b	b	a	b	
		60	c	a	a	a					c	a	b	c	a		b		b	b	b	a	b	c	b	a	b		
	100	20	c	a	a	a	b	b	b	c	a	a	a	a	a	b	a	b	a	a	b	a	b	b	b	a	b	a	
		40		a	a	a	c	c	c		b	a	b	b	a	c	b	c	b	c	b	a	c	b	b	a	c	a	
		60		a	a	a					c	a	b	c	a		b		b	b	a	a	c	c	c	a	b		
Methoxybenzol	100	20	c	a	a	a	b	c	c	a	c	b	b	b	a	c	c	c	b	c	c	a	c	c	c	a	c	c	
		40		b	b	a	c			b		b	c	c	a				b			a				b			
		60		b	b	a				b					a				b			a				b			
2-Methoxyethanol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	b	a	a	a	a	b	b	a	a	a	
		40	a	a	a	a	a	a	a	a	c	a	a	b	a	b	a	b	a	a	a	a	a	c	c	a	a	a	
		60	a	a	a	a	a	a	a	a	a	a	c	a	b	a	b	a	a	a	a	a	a		a	a	a	a	
Methylacetat	100	20	c	a	a	a	c	c	c	a	c	b	b	c	a	c	a	b	a	b	c	c	a	b	c	c	c	c	
		40		b	b	a				a		b	c		a		a	c	b			a	c						
		60		b	b	a				a		b			a		a		c			a							
Methylalkohol	100	20	b	a	a	a	b	a	a	c	b	a	a	a	a	a	b	a	b	a	b	b	a	b	b	a	a	b	
		40	c	a	a	a	c	a	a		c	a	a	b	a	c	a	b	a	c	c	a	c	c	b	a	c	b	
		60		a	a	a		a	b			a	a	c	a		a	b	a			a		b	a	a	b		
Methylamin	100	20	b	a	a	a	c	c	c	c	c	a	b	c	a	a	a	a	a	b	c	a	c	c	b	a	b	c	
		40	c	b	b	a						b	b		a	b	b	b	a	c	a			c	a	c			
		60		b	b	a						b	b		a	c	b	c	a			a				a			
Methylbenzol	100	20	c	a	a	a	b	c	c	a	b	b	b	b	a	c	b	c	b	c	c	a	b	c	c	a	c	c	
		40		a	a	a	c			a	c	b																	

Substanz	Konz.%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI
Natriumdithionit	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	c	b	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a
		60	a	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumfluorid	100	20	a	b	b	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	b	b	a	a	a	a	a	b	a	a	b	a	a	a	a	a	a	a	a	b	a	a	a	a	
		60	a	c	c	b	a	a	a	a	b	b	a	b	a	a	a	a	a	a	a	a	b	a	c	c	a	a
Natriumhydrogencarbonat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	
		60	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	b	b	a	a
di-Natriumhydrogenphosphat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumhydrogensulfat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	b	b	a	b	b	a	b	b	b	a	a	b	a	b	a	a	a	a	
		60	a	a	a	a	a	a	a	c	c	a	c	b	a	c	c	c	c	a	a	c	a	b	b	b	a	a
Natriumhydrogensulfid	40	20	a	a	a	a	a	a	a	b	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	b	b	a	a		b	a	a	b	a	b	a	a	a	a	
		60	a	a	a	a	a	a	a	c	a	c	b	a	a	a	c	c	a	a	c	a	b	b	b	a	a	a
Natriumhydroxid	15	20	b	a	a	a	b	a	b	b	c	a	a	c	a	b	a	a	a	b	a	a	b	b	b	a	b	
		40	b	a	a	a	b	a	b	b	b	a	a	a	a	c	a	a	a	a	b	b	a	b	c	b	a	
		60	b	a	a	a	c	b	c	c		b	b		a		a	b	b	b	b	a	c		c	a	b	
	50	20	b	a	a	a	b	a	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	a	b	
		40	b	a	a	a	c	b		b	b	b	b	a	a		a		b	b	b	a	b	b	c	c	b	
		60	c	a	a	a	c		c		c	c		a		a		a		c	c	b	a	c		b	c	
	100	20	b	a	a	a	b	b	c	b	c	a	a	c	a	c	a	c	a	c	b	a	a	b	b	b	a	b
		40	c	a	a	a	c	c		c		c	b	b	a	a		a		b	c	b	a	c	c	c	b	c
		60	a	a	a							c	c		a		a		c		c	a				b		
Natriumhypochlorit	20	20	a	a	a	a	b	b	b	c	b	a	a	b	a	c	a	c	b	a	a	a	b	b	a	a	a	
		40	a	a	a	a	c	c	c		c	a	a	c	a	a		a		b	a	a	a	c	c	a	a	
		60	a	a	a	a						c	a	a	a	a		a		c	a	a	a		b	a	a	
Natriumhypodisulfit	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumhyposulfid	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumnitrat	100	20	b	a	a	a	b	b	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	a	b	
		40	c	a	a	a	c	c		c		b	b		a		a		b	c	b	a	c	c	c	b	c	
		60	a	a	a							c	c		a		a		c		c	a			b			
Natriumnitrit	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumperborat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	b	b	a	a	b	b	b	a	a	b	a	b	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	c	b	a	a	c		a	a	c	a	b	b	b	a	a	a
Natriumperchlorat	25	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	b	b	b	a	a	b	a	b	b	b	a	a	b	a	b	a	a	a	b
		60	a	a	a	a	a	a	b	b	c	a	a	b	a	b	b	b	b	a	a	b	a	b	a	a	a	b
Natriumperoxid	100	20	a	a	a	a	b	a	b	a	a	a	a	a	a	b	b	c	b	a	a	a	a	a	a	a	a	
		40	a	a	a	a	b	a	c	b	b	a	a	b	a	c	c		b	a	b	a	b	b	b	c	a	
		60	a	a	a	a	b	a	b	c	a	a	b	a	a	a	a		b	a	b	a	b	c	c	a	a	
Natriumperoxodisulfat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumpersulfat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
mono-Natriumphosphat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a
di-Natriumphosphat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a
Natriumsilicat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumsulfat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a
Natriumsulfid	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumsulfit	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumsuperoxid	100	20	a	a	a	a	b	a	b	a	a	a	a	a	a	b	b	c	b	a	a	a	a	a	a	a	b	
		40	a	a	a	a	b	a	c	b	b	a	a	b	a	c	c		b	a	b	a	b	b	b	a	c	
		60	a	a	a	a	b	a	b	c	a	a	a	b	a	a	a		b	a	b	a	b	c	c	a	a	
Natriumtetraborat	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	b	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	b	a</																				

Substanz	Konz.-%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI
Natriumthiosulfat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60	a	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a
Natriumtrisilicat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Natron	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	
		60	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	b	b	a	a
Natronlauge	15	20	b	a	a	a	b	a	b	b	c	a	a	c	a	b	a	a	a	b	a	a	b	b	b	a	b	
		40	b	a	a	a	b	a	b	b	b	a	a		a	c	a	a	a	b	b	a	b	c	c	b	b	
		60	b	a	a	a	c	b	c	c	c	b	b		a	a	a	b	b	b	b	a	c	c	b	a	b	
	50	20	b	a	a	a	b	a	c	b	c	a	a	c	a	c	a	c	a	b	a	a	b	b	b	a	b	
		40	b	a	a	a	c	b		b	b	b	b		a		a		b	b	b	a	b	c	c	b	b	
		60	c	a	a	a	c	b		c	c	c	c		a		a		c	c	b	a	c			b	c	
Natronwasserglas	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a
Nickelchlorid	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	a	a	b	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Nickelnitrat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a
Nickelsulfat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40	a	a	a	a	a	a	a	c	b	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60	a	a	a	a	a	a	a	a	c	a	a	b	a	a	a	a	a	a	b	a	b	a	a	a	a	a
2,2',2''-Nitrilotriethanol	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	b	a	a	b	b	a	a	
		40	b	a	a	a	a	b	a	b	a	a	b	a	b	b	b	c	a	b	c	a	b	b	b	a	b	
		60	b	a	a	a	a	a	b	a	b	a	a	b	a	b	b	b	a	b	c	a	b	b	c	c	a	b
Nitrobenzol	100	20	c	a	a	a	b	b	c	b	c	b	c	c	a	c	c	c	c	c	c	a	b	c	b	a	c	
		40		b	b	a	c	b		c		c			a							a	c		c	b		
		60		b	b	a	c	b		c		c			a							a	c		c	b		
Nitroverdünner	100	20	c	a	a	a	a	b	b	c	a	a	b	a	c	b	b	a	c	b	a	b	c	b	a	c	b	
		40		a	a	a	b	a	b	c		a	b	c	a		b	b	b		c	a	c		c	a	b	
		60		a	a	a	c	a	c		b	b		a		a	c	c	b		a		a			a	c	
1-Nonanol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	
		60	b	a	a	a		c	a			a	a	c	a		b	a	a	b		a			c	a	b	
Octadecansäure	100	20	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	
		40	b	a	a	a	b	a	a	b	b	a	a	b	a	b	a	a	a	b	b	a	b	b	b	a	b	
		60	b	a	a	a	c	a	a	b	b	a	a	b	a	b	a	a	a	b	b	a	b	b	b	a	b	
Octan	100	20	c	a	a	a	b	a	a	b	a	a	a	a	b	a	a	a	c	b	a	b	c	b	a	c	a	
		40		a	a	a	c	b	a	a	c	a	a	b	a	b	a	a	a	c	a	a	c		c	a	b	
		60		a	a	a		c	c	a		a	a	c	a	b	a	a	a		a						a	c
Öl (Erdöl)	100	20	c	b	b	a	a	b	c	a	b	b	c	b	a	c	c	c	b	c	b	a	a	c	b	a	c	
		40		c	c	a	b	c		b	c	c		b	a				c		c	a	b		c	a		
		60				b	c			c				c	b								b	c		b		
Öl (etherisches Öl)	100	20	c	a	a	a	a	b	b	a	b	b	b	a	a	b	b	b	b	c	b	a	b	c	b	a	c	
		40		a	a	a	a	b	c	b	b	b	c	b	a	c	c	c	b		b	a	b		c	a		
		60		a	a	a	a	b		b	c	c		b	a				c	c	a	c				a		
Öl (fettes Öl)	100	20	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	
		40	b	b	b	a	a	a	b	a	b	a	a	b	a	b	a	a	a	b	b	a	b	a	a	a	b	
		60	b	b	b	a	a	a	c	a	c	a	b	c	a	c	b	a	b	b	b	a	b	b	a	a	b	
Öl (Heizöl)	100	20	c	a	a	a	a	b	c	a	b	b	b	b	a	c	b	a	a	c	b	a	b	c	b	a	c	
		40		a	a	a	b	c		a	b	b	c	b	a	c	b	a	b		b	a	b		c	a		
		60		a	a	a	c			a	b	b		b	a		b	b	b		b	a	b			a		
Öl (Maschinenöl, aromatenfrei)	100	20	b	a	a	a	a	b	c	a	a	a	b	a	a	b	a	b	a	b	a	a	a	c	b	a	b	
		40	b	a	a	a	b	b		a	b	b	c	b	a	c	b	c	b	b	a	a	b		b	a	b	
		60	c	a	a	a	b	c		a	b	b		b	a		b		b	c	a	a	b		c	a	c	
Öl (Mineralöl)	100	20	b	a	a	a	a	b	c	a	a	a	b	a	a	b	a	a	a	b	a	a	a	c	b	a	b	
		40	b	a	a	a	b	b		a	b	b	c	b	a	c	b	a	b	b	a	a	b		b	a	b	
		60	c	a	a	a	b	c		a	b	b		b	a		b	a	b	c	a	a	b		c	a	c	
Öl (Schmieröl)	100	20	b	a	a	a	a	b	c	a	a	a	b	a	a	b	a	a	a	b	a	a	a	c	b	a	b	
		40	b	a	a	a	b	b		a	b	b	c	b	a	c	b	a	b	b	a	a	b		b	a	b	
		60	c	a	a	a	b	c		a	b	b		b	a		b	a	b	c	a	a	b		c	a	c	
Öl (Siliconöl)	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	
		40	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	b	a	a	a	b	a	a	
		60	b	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	a	c	a	a	b	
Oleinsäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	c	
		40		a	a	a	a	a		a	b	b		a	a		b	b	c		b	a	b	a	a	a		
		60		a	a	a	a	a		a	c	c		b	a		c	c			c	a	c	a	a	a		
Oleum	100	20	c	c	c	a	c	b	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	c	c	c	c	
		40				a		c							a							a						
		60				a									a							a						
Ölsäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	c	
		40		a	a	a	a	a		a	b	b		a	a		b	b	c		b	a	b	a	a	a		
		60		a	a	a	a	a		a	c	c		b	a		c	c			c	a	c	a	a	a		
Oxalsäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	c	
		40		a	a	a	a	a		a	b	b		a	a		b	b	c		b	a	b	a	a	a		
		60		a	a	a	a	a		a	c	c		b	a		c	c			c	a	c	a	a	a		

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI
			Oxiran	100	20	c	a	a	a	c	b	c	a	b	a	b	c	a	c	b	c	b	c	a	a	b	b	a
		40		a	a	a				a	c	b	b		a				b		a	a	c	c	a	a		
		60		a	a	a		c		a		b	b		a				b		a	a	c	c	a	a		
Oxolan	100	20	c	b	b	a	a	a	c	a	c	b	b	a	a	c	b	a	b	c	c	a	a	c	c	b	c	
		40		b	b	a	b	b		a		b	b	a	a		c	b	b			a	a		b	b		
		60		c	c	a	b	b		a		b	c	b	a		c	b	b			a	a		c	c		
Ozon	100	20	b	a	a	a	a	b	c	a	a	a	a	a	a	b	a	b	a	b	a	a	a	c	b	b	a	b
		40	b	a	a	a	b	b		b	b	a	b	b	a	c	a	b	b	b	b	a	a	c	c	c	a	b
		60	c	a	a	a	c	c		c	c	a	b	c	a		a	b	b	c	a	a	c	c	c	a	c	
Palmitinsäure	100	20	c	a	a	a	a	a	c	a	b	b	c	a	a	c	a	a	b	c	b	a	b	a	a	a	a	c
		40		a	a	a	a	a		a	b	b		a	a		b	b	c		b	a	b	a	a	a		
		60		a	a	a	a	a		c	c	c		b	a		c	c			c	a	c	a	a	a		
Paraffinöl	100	20	c	b	b	a	a	c	c	a	a	b	b	a	a	c	b	a	b	c	b	a	a	c	a	a	c	
		40		b	b	a	a			a	a	b	c	b	a		b	b	b		b	a	a		a	a		
		60		c	c	a	a			a	a	b		b	a		c	b	c		c	a	a		a	a		
1-Pentanol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	a	b	a	b	b	b	a	a
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	
		60	b	a	a	a		c	a		a	a	c	a	a		b	a	a	b		a		c	a	b	b	
3-Pentanon	100	20	c	b	b	a	b	c	a	c	b	b	c	a	c	c	b	c	b	c	c	a	b	c	c	c	c	
		40		b	b	a	c	c		a		b	c	a		c	c		b		a	c						
		60		c	c	a				a		b		a					b			a						
Pentylacetat	100	20	c	a	a	a	a	c	a	c	a	a	b	a	a	b	a	a	a	c	c	a	c	c	c	a	c	
		40		a	a	a	a	b		a		a	a	c	a	b	c	a	a			a				a		
		60		a	a	a	a	b		a		a	a		a	b		a	a			a				a		
Pentylalkohol	100	20	a	a	a	a	c	b	a	b	b	a	a	a	a	b	a	a	a	a	b	a	b	b	b	a	a	b
		40	b	a	a	a		b	a	c	c	a	a	b	a	c	a	a	a	b	c	a	c	c	b	a	b	
		60	b	a	a	a		c	a		a	a	c	a	a		b	a	a	b		a		c	a	b	b	
Perchlorethylen	100	20	c	c	c	a	a	b	c	a	c	b	c	a	a	c	c	a	c	c	c	a	a	c	c	a	c	
		40			b	a	b			a	c		a	b				b			b	a			b			
		60			b	a	b			a			a	b				c				b	a		b			
Perchlorsäure	60	20	b	b	b	b	b	b	c	c	c	b	b	c	b	c	b	b	b	b	c	b	c	c	b	a	b	c
		40	c	b	b	b	c					c	c		b		c	c	c	c	b			c	a	c		
		60		c	c	c		c							c							c			a	c		
Perhydronaphthalin	100	20	c	a	a	a	c	b	b	a	c	a	b	c	a	b	c	a	b	c	c	a	c	c	a	a	c	
		40		a	a	a		c	c	a		b	b		a	c		b	b			a			b	a		
		60		a	a	a				a		b	c		a			b	c			a			a	a		
Petrol	100	20	c	b	b	a	a	c	c	a	a	b	b	a	a	a	b	a	b	b	c	b	a	a	c	a	a	c
		40		b	b	a	a			a	a	b	c	b	a	a	b	b	b		b	a	a		a	a		
		60		c	c	a	a			a	a	b		b	a	a	c	b	c		c	a	a		a	a		
Petrolether	100	20	c	a	a	a	c	b	c	a	c	b	c	a	a	c	c	c	c	c	c	a	c	c	b	a	c	
		40		b	b	a		c		a		c		b	a						a			c	b			
		60		b	b	a				b				c	a							a			b			
Phenol	100	20	c	a	a	a	b	b	c	c	c	c	c	c	a	c	c	c	c	c	c	a	c	b	b	a	c	
		40		b	b	a	c	b		a				a							a		c	c	a	c		
		60		c	c	a		b						a								a			a			
Phenylameisensäure	100	20	b	a	a	a	a	b	c	c	a	a	a	a	a	b	a	b	a	b	b	a	a	a	a	a	b	
		40	b	a	a	a	b	c			b	a	a	b	a	c	b	b	b	b	b	a	b	b	b	a	b	
		60	b	a	a	a	c				b	a	a	c	a	b	c	b	b	c	a	c	b	b	a	a	b	
Phenylamin	100	20	c	b	b	a	c	c	c	a	c	a	a	c	a	b	b	a	a	c	c	a	c	c	c	a	c	
		40		c	c	a				b	b	b		a	c	b	b	b			a				b			
		60				a				c	c	c	c	a	a	c	c	c			a				c			
Phenylethan	100	20	c	b	b	a	b	c	c	a	c	b	b	b	a	c	b	c	b	c	c	a	c	c	c	b	c	
		40		b	b	a	c			a		b	c	c	a						a				b			
		60		c	c	a				a												a				c		
Phenylether	100	20	c	a	a	a	c	b	c	a	c	b	c	c	a	c	c	c	c	c	c	a	c	c	b	a	c	
		40		b	b	a		c		a		c			a							a			c	b		
		60		b	b	a				b					a							a				b		
Phenylethylen	100	20	c	a	a	a	a	b	c	a	c	b	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	
		40		b	b	a	b	b		b		c	c		a							a				b		
		60		b	b	a	b	b		c					a							a				c		
Phenylmethanol	100	20	c	a	a	a	b	c	c	c	b	b	c	c	a	c	c	a	c	c	c	a	b	c	b	a	c	
		40		a	a	a	c				c	c			a						a	c		c	a			
		60		a	a	a									a						b				a			
2-Phenylpropan	100	20	c	a	a	a	b	b	c	a	c	b	b	c	a	c	c	c	b	c	c	a	c	c	a	c	c	
		40		b	b	a	c	c		b		b	b		a						c				a	b		
		60		b	b	a				b		c	c		a							a				b		
Phosphor(III)chlorid	100	20	c	a	a	a	a	b	c	b	b	a	b	b	a	c	b	c	b	c	b	a	b	c	c	a	c	
		40		a	a	a	b	b		c	c	a	b	c	a		c	b	b	c	a	c			a			
		60		a	a	a	c	c				a	b		a				b			a			a			
ortho-Phosphorsäure	5	20	b	a	a	a	b	a	b	c	a	a	a	a	a	c	a	c	a	b	b	a	b	a	a	a	b	
		40	c	a	a	a	b	a	b		a	a	a	b	a		a											

Substanz	Konz. %	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI		
1,1,2,2-Tetrachlorethan	100	20	c	c	c	a	a	b	c	a	c	b	c	a	a	c	c	a	c	c	c	a	a	c	c	a	c	c		
		40				b	a	b		a					a	b							b	a			b			
		60				b	a	b		a					a	b							b	a			b			
Tetrachlorethylen	100	20	c	c	c	a	a	b	c	a	c	b	c	a	a	c	c	a	c	c	c	a	a	c	c	a	c	c		
		40				b	a	b		a					a	b							b	a			b			
		60				b	a	b		a					a	b							b	a			b			
Tetrachlorkohlenstoff	100	20	c	a	a	a	a	b	c	c	c	b	b	c	a	c	c	b	b	c	c	a	c	c	b	a	c	c		
		40		a	a	a	b	b					b	c		a							a			c	a			
		60		a	a	a	c	b							a								a				a			
Tetrachlormethan	100	20	c	a	a	a	a	b	c	c	c	b	b	c	a	c	c	b	b	c	c	a	c	c	b	a	c	c		
		40		a	a	a	b	b					b	c		a							a			c	a			
		60		a	a	a	c	b							a								a				a			
Tetrahydrofuran	100	20	c	b	b	a	a	a	c	a	c	b	b	a	a	c	b	a	b	c	c	a	a	c	c	b	c	c		
		40		b	b	a	b	b		a		b	b	b	a			b	b	b			a	b			b			
		60		c	c	a	b	b		a		b	c	b	a								a	b			c			
1,2,3,4-Tetrahydronaphthalin	100	20	c	a	a	a	c	b	b	a	c	a	b	c	a	b	c	a	b	c	c	a	c	c	a	a	c	c		
		40		a	a	a		c	c	a		b	b		a	c			b	b			a			b	a			
		60		a	a	a				a		b	c		a				b	c			a			c	a			
Tetralin	100	20	c	a	a	a	c	b	b	a	c	a	b	c	a	b	c	a	b	c	c	a	c	c	a	a	c	c		
		40		a	a	a		c	c	a		b	b		a	c			b	b			a			b	a			
		60		a	a	a				a		b	c		a				b	c			a			c	a			
THF	100	20	c	b	b	a	a	a	c	a	c	b	b	a	a	c	b	a	b	c	c	a	a	c	c	b	c	c		
		40		b	b	a	b	b		a		b	b	b	a			b	b	b			a	b			b			
		60		c	c	a	b	b		a		b	c	b	a				b	c			a	b			c			
Thionylchlorid	100	20	c	a	a	a	c	b	c	c	c	c	c	c	a	c	c	b	c	c	c	a	c	c	c	b	c	c		
		40		a	a	a		c							a								a				b			
		60		a	a	a									a								a				b			
Toluol	100	20	c	a	a	a	b	c	c	a	b	b	b	a	a	c	b	c	b	c	c	a	b	c	c	a	c	c		
		40		a	a	a	c			a	c	b	c	b	a				b				a	c			a			
		60		a	a	a				a		b	c	b	a								a	c			a			
Tonerde	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	b	a	b	a	b	a	a	a	a	a	a	b	b		
		40		b	a	a	a	b	b	c	b	b	b	b	b	a	c	a	c	a	b	a	a	a	a	a	a	a	b	c
		60		b	a	a	a	c	c	c	c	c	b	b	a	b	a						b	a	a	a	a	a	a	b
Tonerde Hydrat	100	20	b	a	a	a	b	b	c	a	b	a	a	b	a	b	a	a	a	b	b	a	b	a	a	a	a	b	a	
		40		b	a	a	a	c	c		b	c	a	a	c	a	c	b	a	a	b	b	a	c	a	a	a	a	b	a
		60		b	a	a	a				c		a	b		a			b	a	a	b	b	a	a	a	a	a	b	a
Tonerde, essigsauer	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	b	a	b	a	b	a	a	b	a	a	a	a	a	a	
		40		a	a	a	a	b	b	b	b	b	a	a	a	a	b	a	c	a	b	a	a	c	a	a	a	a	a	
		60		a	a	a	a	c	c	c	b	b	a	a	b	a	c	a		a	b	a	a		a	a	a	a	a	b
Traubenzucker	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Trichloracetaldehydhydrat	100	20	c	a	a	a	a	c	c	c	b	b	b	c	a	c	b	c	b	c	c	a	c	b	a	a	c	c		
		40		a	a	a	b					c	b	b		a							a			c	b	a		
		60		a	a	a	c									a							a				b	a		
1,2,4-Trichlorbenzole	100	20	c	a	a	a	b	b	c	b	c	c	c	b	a	c	b	c	c	c	c	a	b	c	c	a	c	c		
		40		b	b	a	c	b		b					c	a							a	c			a			
		60		b	b	a		c		b						a							a				a			
Trichloressigsäure	100	20	b	a	a	a	c	b	b	c	b	b	b	c	a	b	a	a	b	b	b	a	b	b	b	a	b	c		
		40		c	b	b	a	b	c		c	b	c		a	c	a	a	c	c	b	a	c	c	c	a	c			
		60		c	c	a		b							a			a	a				b	a			a			
Trichlorethylen	100	20	c	a	a	a	c	b	c	a	c	b	c	b	a	c	c	c	c	c	c	a	b	c	c	a	c	c		
		40		b	b	a		b		a		c		b	a								a	b			a			
		60		b	b	a		c		a						c	a						a	c			a			
Trichlormethan	100	20	c	b	b	a	c	c	c	b	c	a	a	c	a	c	c	a	a	c	c	a	c	c	c	a	c	c		
		40		c	c	a				c		b	b		a			b	b				a				a			
		60				a							c	c	a				b	c			a				a			
Triethanolamin	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	b	a	a	b	b	a	a	a		
		40		b	a	a	a	a	a	b	a	b	a	a	b	a	b	b	c	a	b	c	a	b	b	b	a	b	a	
		60		b	a	a	a	a	a	b	a	b	a	a	b	a	b	b		a	b		a	b	c	c	a	b	b	
Triethylenglykol	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	b	b	b	a	a	a	
		40		b	a	a	a	b	a	a	a	b	a	a	b	a	b	a	a	a	b	a	a	b	c	b	a	b	a	
		60		b	a	a	a	c	a	a	a	b	a	a	c	a	b	a	b	a	b	a	a	c		c	a	b	a	
Triglykol	100	20	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	b	b	b	a	a	a		
		40		b	a	a	a	b	a	a	a	b	a	a	b	a	b	a	a	a	b	a	a	b	c	b	a	b	a	
		60		b	a	a	a	c	a	a	a	b	a	a	c	a	b	a	b	a	b	a	a	c		c	a	b	a	
2,2,4-Trimethylpentan	100	20	c	a	a	a	b	a	a	a	b	a	a	a	a	b	a	a	a	c	b	a	b	c	b	a	c	a		
		40		a	a	a	c	b	b	a	c	a	a	b	a	b	a	a	a	c	a	c				c	a	b		
		60		a	a	a		c	c	a		a	a	b	a	b	a	b	a	a			a				a		c	
Tris-(2-hydroxyethyl)amin	100	20	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a	a	b	a	a	b	b	a	a	a		
		40		b	a	a	a	a	a	b	a	b	a	a	b	a	b	b	c	a	b	c	a	b	b	b	a	b	a	
		60		b	a	a	a	a	a	b	a	b	a	a	b	a	b	b		a	b	c	a	b	b	c	c	a	b	b
Urin	100	20	a	a	a	a	a	a	c	a	c	a	a	a	a	a	a	a	a	a	a	b	a	a	b	b	a	a	b	
		40		b	a	a	a	a				a	a	a	a	b	b	a	a	b	b	a	a	c	c	a	b	b	b	
		60		b	a	a	a	a	a			a	a	a	a	a	b	b	a	a	b	c	a	a			a	b	c	
Vaseline	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a		
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		60		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
Verdünner	100	20	c	a	a	a	a	a	b	b	c	a	b	c	a	c	b	b	b	c	c	a	b	c	b	a	c	b		
		40	</																											

Substanz	Konz.%	Temp. °C	ABS	ECTFE	ETFE	FEP	GFK	MF	NR	PA	PC	PE-HD	PE-LD	PET	PFA	PMMA	PMP	POM	PP	PS	PSU	PTFE	PUR	PVC-P	PVC-U	PVDF	SAN	SI	
Vinylacetat	100	20	c	b	b	a	b	b	c	c	c	b	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	
		40		b	b	a	b	b								a							a				a		
		60		c	c	a	c	c								a							a				a		
Vinylbenzol	100	20	c	a	a	a	a	b	c	a	c	b	b	c	a	c	b	a	b	c	c	a	c	c	c	a	c	c	
		40		b	b	a	b	b			b		c	c				c	b	c			a				b		
		60		b	b	a	b	b			c					a							a					c	
Vinylchlorid	100	20	c	b	b	a	b	b	c	c	c	b	c	c	a	c	c	c	c	c	c	a	c	c	c	a	c	c	
		40		b	b	a	b	b					c										a				a		
		60		c	c	a	c	c								a							a				a		
Vinylcyanid	100	20	c	a	a	a	b	c	c	a	c	a	a	c	a	c	b	c	b	c	c	a	c	c	c	b	c	c	
		40		a	a	a	b			a		a	a	a		a		b		c			a				b		
		60		a	a	a	c					b	b	a		a							a					c	
Vinylethylen	100	20	c	a	a	a	a	c	c	c	b	c	b	c	a	a	c	a	c	c	c	a	a	c	b	a	c	c	
		40		a	a	a	b				b		c			b	a		a				a	b		c	a		
		60		a	a	a	c				c					c	a		a				a	c			a		
Waschmittel	5	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a
Wasser	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		a	a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a
Wasser entmineralisiert	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		b	a	a	a	b	b	b	b	b	b	b	b	b	a	b	a	a	b	b	b	a	b	b	b	a	b
Wasserglas	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a
Wasserstoffperoxid	5	20	a	a	a	a	b	a	b	c	a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	
		40		b	a	a	a	c	a	b		a	a	a	b	a	b	a		a	b	a	a	a	b	a	a	b	a
		60		b	a	a	a		a	b		a	a	a	b	a	b	a		a	b	a	a	b	b	a	a	b	a
	30	20	a	a	a	a	b	a	b	c	a	a	a	a	a	a	c	a	c	a	a	a	a	a	b	a	a	a	b
		40		b	a	a	a	c	b	c		a	a	b	b	a		b		b	b	a	a	b	c	a	a	b	b
		60		b	a	a	a		b			a	a	b	b	a		b		b	b	a	a	b		a	a	b	c
Wasserstoffsperoxid	5	20	a	a	a	a	b	a	b	c	a	a	a	a	a	a	a	a	c	a	a	a	a	a	a	a	a	a	
		40		b	a	a	a	c	a	b		a	a	a	b	a	b	a		a	b	a	a	a	b	a	a	b	a
		60		b	a	a	a		a	b		a	a	a	b	a	b	a		a	b	a	a	a	b	b	a	a	b
	30	20	a	a	a	a	b	a	b	c	a	a	a	a	a	a	c	a	c	a	a	a	a	a	b	a	a	a	b
		40		b	a	a	a	c	b	c		a	a	b	b	a		b		b	b	a	a	b	c	a	a	b	b
		60		b	a	a	a		b			a	a	b	b	a		b		b	b	a	a	b		a	a	b	c
Weinsäure	100	20	b	a	a	a	a	a	b	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a	a	a	a	b	
		40		b	a	a	a	a	a	c	b	b	a	a	a	a	c	a	b	a	b	a	a	a	a	b	b	a	b
		60		b	a	a	a	a	a		b	b	a	a	b	a		a	b	a	b	a	a	b	b	b	a	b	b
Wollfett	100	20	a	a	a	a	a	a	a	a	a	a	b	a	a	a	b	a	a	a	a	a	a	a	b	b	a	a	
		40		a	a	a	a	a	b	b	a	a	b	b	b	a	b	b	b	a	a	a	a	a	a	b	b	a	a
		60		b	a	a	a	a	b	b	b	b	b	b	b	a	b	b	b	a	b	a	a	a	b	b	a	b	b
p-Xylol	100	20	c	a	a	a	a	a	c	a	c	b	b	a	a	c	b	b	b	c	c	a	a	c	c	a	c	c	
		40		b	b	a	a	b					b	c	b	a		c	c	c									
		60		b	b	a	a	b				a		c		c	a						a	a					
Zinkcarbonat basisch	100	20	b	a	a	a	b	a	a	b	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	b	a
		40		b	a	a	a	c	a	a	c	b	a	b	b	a	b	a	b	a	b	b	a	b	b	a	a	b	a
		60		b	a	a	a		a	a		b	a	b	b	a	b	a	b	a	b	b	a	b	b	b	a	b	a
Zinkchlorid	100	20	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		a	a	a	a	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a
Zinkhydroxidcarbonat	100	20	b	a	a	a	b	a	a	b	a	a	a	a	a	a	a	a	a	b	b	a	a	b	b	a	a	b	a
		40		b	a	a	a	c	a	a	c	b	a	b	b	a	b	a	b	a	b	b	a	b	b	a	a	b	a
		60		b	a	a	a		a	a		b	a	b	b	a	b	a	b	a	b	b	a	b	b	b	a	a	b
Zinknitrat	100	20	a	a	a	a	a	a	a	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	
		40		a	a	a	a	a	a	a	c	b	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a	a
		60		a	a	a	a	a	a	a		c	a	a	a	a	a	a	a	a	a	a	b	a	b	a	a	a	a